

TCS Mo-based Alloys Mobility Database (MOBMO2)

Technical Information

Available Starting with Thermo-Calc Version 2025b



Contents

MOBMO2: TCS Mo-based Alloys Mobility Database	3
The CALPHAD Method	3
Additional Resources	4
MOBMO2 Elements and Phases	5
Included Elements	5
Included Phases	5
Limits	6
MOBMO2 Assessed Systems	7
Binary Systems	7
Ternary Systems	8
Compounds	8
MOBMO: TCS Mo-based Alloys Mobility Database Revision History	9

MOBMO2: TCS Mo-based Alloys Mobility Database

Molybdenum-based alloys are used in various applications due to their excellent mechanical, thermal, and corrosion-resistant properties. They are commonly used in aerospace components, electrical contacts, industrial machinery, and high-temperature furnace parts. Additionally, they are used in the production of high-strength steel alloys, which are crucial in construction and automotive industries for their durability and resistance to corrosion and heat.

The TCS Mo-based Alloys Mobility Database (MOBMO) is a kinetic database containing atomic mobility data for Mo-based refractory alloys. The database is compatible and primarily recommended for use with the most recent version of the TCS Mo-based Alloys Database (TCMO) (i.e. TCMO2).

The Mo-based alloys thermodynamic and kinetic databases (i.e. TCMO2 and MOBMO2) are available for refractory (e.g. Mo-base) superalloys that function at higher temperatures than the Ni-base superalloys. The Mo databases include the silicide and borosilicide phases to form SiO_2 -based scales, which is to overcome the challenge of poor oxidation resistance that happens with these alloys that contain MoO_3 .

The MOBMO2 database provides kinetic data for those working with the Add-on Modules—the Diffusion Module (DICTRA) and the Precipitation Module (TC-PRISMA). It can also be used together with the Thermo-Calc Software Development Kits (SDKs).

When the kinetic database is used with the Diffusion Module (DICTRA), and a thermodynamic database for Mo-based alloys (e.g. TCMO2) you can study diffusion-controlled phenomena in Mo/substrate systems, such as solidification, growth of interfacial compounds, dissolution of substrates, interdiffusion, and much more. Similarly, when used with the Precipitation Module (TC-PRISMA), it is suitable to simulate concurrent nucleation, growth, and coarsening of precipitates in Mo alloys.



[MOBMO: TCS Mo-based Alloys Mobility Database Revision History](#). The current version of the database is MOBMO2. See the link for any subversion release details.

| The CALPHAD Method

The Thermo-Calc databases are developed with the CALPHAD approach based on various types of experimental data and theoretical values (e.g. those from first-principles calculations). It is based on the critical evaluation of binary, ternary, and for some databases, important higher order systems. This enables predictions to be made for multicomponent systems and alloys of industrial importance. Among these, the thermodynamic database is of fundamental importance.



For more learning resources about CALPHAD and our databases, visit the video tutorials on our [website](#) or our [YouTube playlist](#).



Learn more on our website about the [CALPHAD Method](#) and how it is applied to the Thermo-Calc databases.

Additional Resources



Go to the [Molybdenum-based Alloys Databases](#) page on our website where you can access this Technical Information plus learn more about the compatible thermodynamic database and its Validation and Calculation Examples Collection.

MOBMO2 Elements and Phases

Included Elements

There are 19 elements included in the most recent version of the database.

Included Elements									
Al	B	C	Cr	Fe	Hf	Mn	Mo	Nb	Pt
Re	Rh	Ru	Si	Ta	Ti	V	W	Zr	

Included Phases

Solution Phases

Solution Phases				
FCC_A1	BCC_A2	BCC_B2	HCP_A3	LIQUID

Compound Phases

Compound Phases				
MO5SI3_D8M	C15_LAVES	M6C	MOSI3_A15	MOSI2_C11B



The phases have diffusion data included in the database. You can include other phases in a diffusion simulation. However, these other phases are treated as so-called diffusion `NONE`, i.e. there is no diffusion considered in these other phases. Any phase not listed above is automatically entered as diffusion `NONE` (in Console Mode in the DICTRA module or in Graphical Mode with the Diffusion Module (DICTRA) and/or Precipitation Module (TC-PRISMA)), as long as a thermodynamic description for the phases is retrieved prior to reading data from the mobility database.

| Limits

As in the spirit of the CALPHAD method, predictions can be made for multicomponent systems by extrapolation into multicomponent space of data critically evaluated and assessed based on binary, ternary and in some cases higher order systems. However, critical calculations must always be verified by equilibrium experimental data; it is the user's responsibility to verify the calculations but Thermo-Calc Software AB is interested to know about any significant deviations in order to improve any future release.

MOBMO2 Assessed Systems

The following systems have been either critically or tentatively assessed in this version of the database.

- 49 binary systems
- 15 ternary systems for solid phases
- 3 compounds



Parameters for self- and impurity- diffusivity of all the elements in the liquid phase are estimated using the Modified Sutherland equation. Mobility data for MO3SI_A15 are MOSI2_C11B are estimated.

Binary Systems

BCC_A2

Binary Systems (BCC_A2)					
Al-Fe	Al-Nb	Al-Ti	Cr-Fe	Cr-Mo	Cr-Nb
Cr-Ta	Cr-Ti	Fe-Mn	Fe-Mo	Fe-Si	Fe-Ti
Fe-V	Hf-Mo	Hf-Nb	Hf-Ta	Hf-Ti	Hf-Zr
Mn-Ti	Mn-V	Mn-Zr	Mo-Nb	Mo-Ta	Mo-Ti
Mo-W	Mo-Zr	Nb-Ta	Nb-Ti	Nb-V	Nb-W
Nb-Zr	Ta-Ti	Ta-W	Ta-Zr	Ti-V	Ti-W
V-Zr	Zr-Ti				

FCC_A1

Binary Systems (FCC_A1)					
Al-Cr	Al-Fe	Al-Pt	Al-Si	Al-Ti	Cr-Fe
Fe-Mn	Fe-Si				

HCP_A3

Binary Systems (HCC_A3)

C-Mo	Cr-Fe	Fe-Zr
------	-------	-------

Ternary Systems

BCC_A2

Ternary Systems (BCC_A2)

Fe-Cr-Mo	Fe-Mn-Si	Ti-Al-Cr	Ti-Al-Fe	Ti-Al-Mo	Ti-Al-Nb
Ti-Al-Zr	Ti-Cr-Nb	Ti-Mo-Ta	Ti-Nb-Ta	Ti-Nb-V	Zr-Ta-Nb
Zr-Ti-Nb					

FCC_A1

Ternary Systems (FCC_A1)

Fe-Mn-Si	Fe-Cr-C
----------	---------

Compounds

Compounds

Compounds

MO5SI3_D8M: Mo ₅ Si ₃	C15_LAVES: ZrMo ₂	M6C: Fe ₃ Mo ₂ C
---	------------------------------	--

MOBMO: TCS Mo-based Alloys Mobility Database Revision History

Current Database Version

Database name (acronym):	TCS Mo-based Alloys Mobility Database (MOBMO)
Database owner:	Thermo-Calc Software AB
Database version:	2.0
First release:	MOBMO1 was released with 2024b

Changes in the Most Recent Database Release

MOBMO1 to MOBMO2

Software release version 2025b (June 2025)

NEW ELEMENTS

- Seven (7) new elements added to the database to align with the thermodynamic database: Nb, Pt, Rh, Ru, Ta, V, and W. Now it is a 19 element framework.
- Parameters for the new elements Nb, Pt, Rh, Ru, Ta, V, and W in the liquid phase are estimated using the Modified Sutherland equation.

BINARY SYSTEMS

- Twenty-one (21) newly assessed binary systems for BCC_A2 phase (total 38): Al-Nb, Cr-Nb, Cr-Ta, Fe-V, Hf-Nb, Hf-Ta, Mn-V, Mo-Nb, Mo-Ta, Mo-W, Nb-Ta, Nb-Ti, Nb-V, Nb-W, Nb-Zr, Ta-Ti, Ta-W, Ta-Zr, Ti-V, Ti-W, and V-Zr.
- One (1) newly assessed binary system for FCC_A1 phase (total 8): Al-Pt

TERNARY SYSTEMS

- Seven (7) newly assessed ternary systems for BCC_A2 phase: Ti-Al-Nb, Ti-Cr-Nb, Ti-Mo-Ta, Ti-Nb-Ta, Ti-Nb-V, Zr-Ta-Nb, and Zr-Ti-Nb.