

SSOL7: SGTE Solutions Database

<i>Database name:</i>	SGTE Solutions Database	<i>Database acronym:</i>	SSOL
<i>Database owner:</i>	Scientific Group Thermodata Europe (SGTE)	<i>Database version:</i>	7

The SSOL7 SGTE Solutions Database is a thermodynamic database which contains critical assessments for many binary and ternary, and some higher order systems.

This general alloy solutions database is designed for various applications related to alloy design, coatings, joining, heat treatment and inorganic materials. As many as 79 elements have been included in this database.

Included Elements (79)

Ag	Al	Am	As	Au	B	Ba	Be	Bi	C
Ca	Cd	Ce	Co	Cr	Cs	Cu	Dy	Er	Eu
Fe	Ga	Gd	Ge	H	Hf	Hg	Ho	In	Ir
K	La	Li	Lu	Mg	Mn	Mo	N	Na	Nb
Nd	Ni	Np	O	Os	P	Pa	Pb	Pd	Pr
Pt	Pu	Rb	Re	Rh	Ru	S	Sb	Sc	Se
Si	Sm	Sn	Sr	Ta	Tb	Tc	Te	Th	Ti
Tl	Tm	U	V	W	Y	Yb	Zn	Zr	

Developed using the CALPHAD approach, SSOL7 is based on the critical evaluation of binary, ternary and in some cases higher order systems. A total of 843 critically assessed systems (683 binary, 140 ternary and 20 higher-order systems) are included in the SSOL7 database in this 79 elements framework. The complete list of all these critically assessed systems is given in the next section of this document. The command "ASSESSED_SYSTEMS" had been added in the database for all the assessed systems, which enables the users to calculate phase diagrams of these systems using the BINARY and TERNARY modules in Console Mode.

A large number of (1378) phases, including various multicomponent solution phases and many important intermetallic compounds, have been included in SSOL7. The complete list of the phases and their models are attached at the end of this documents. It should be noted that the GAS phase is rejected by default in the database and one should restore it if it is relevant to a calculation.

Order-disorder models, which describe a pair of ordered and disordered phases with a single Gibbs energy function and thus is able to describe a possible 2nd-order transition between the pair of phases, had been employed to some systems, such as BCC_A2/ BCC_B2 in the Al-Fe system and FCC_A1/ FCC_L12 in the Al-Ni system. It should be noted that some B2-type phases had been modeled as stoichiometric phases and thus a separate phase named as “B2_BCC” was created in addition to the BCC_B2 phase in the order-disorder model.

The SSOL7 database enables predictions (such as multi-component phase equilibria and Scheil solidification simulations of industrial alloys) to be made for multicomponent systems and alloys of industrial importance. This means that the SSOL7 database may be utilized to extrapolate to higher-order systems by combining several critically assessed systems. However, such extrapolations require experiences in CALPHAD and a good understanding of the involved systems. And the producer or vendor should be contacted if problems occur.

SSOL7 Assessed Binary Systems

Ag-Al	Ag-Pb	Al-Cr	Al-Ru	Au-C	Au-Zr
Ag-Au	Ag-Pd	Al-Cu	Al-Sb	Au-Co	B-Ba
Ag-B	Ag-Pt	Al-Dy	Al-Sc	Au-Cr	B-C
Ag-Ba	Ag-Rh	Al-Er	Al-Si	Au-Cu	B-Ca
Ag-Be	Ag-Ru	Al-Fe	Al-Sm	Au-Er	B-Co
Ag-Bi	Ag-Sb	Al-Ga	Al-Sn	Au-Fe	B-Cr
Ag-C	Ag-Sc	Al-Gd	Al-Sr	Au-Ga	B-Cu
Ag-Ca	Ag-Si	Al-Ge	Al-Ta	Au-Ge	B-Fe
Ag-Cd	Ag-Sn	Al-Hf	Al-Th	Au-Hf	B-Hf
Ag-Ce	Ag-Sr	Al-Hg	Al-Ti	Au-Ho	B-Mg
Ag-Cr	Ag-Te	Al-Ho	Al-V	Au-In	B-Mn
Ag-Cu	Ag-Ti	Al-In	Al-W	Au-La	B-Mo
Ag-Dy	Ag-Tl	Al-Ir	Al-Y	Au-Ni	B-N
Ag-Er	Ag-V	Al-La	Al-Zn	Au-Pb	B-Nb
Ag-Fe	Ag-W	Al-Li	Al-Zr	Au-Pd	B-Nd
Ag-Ga	Ag-Y	Al-Mg	As-Au	Au-Pr	B-Ni
Ag-Gd	Ag-Zn	Al-Mn	As-Cu	Au-Pt	B-Re
Ag-Ge	Ag-Zr	Al-Mo	As-Ga	Au-Rh	B-Sc
Ag-In	Al-As	Al-N	As-Ge	Au-Ru	B-Si
Ag-Ir	Al-Au	Al-Nb	As-In	Au-Sb	B-Sr
Ag-Mg	Al-B	Al-Nd	As-Ni	Au-Si	B-Ti
Ag-Mn	Al-Be	Al-Ni	As-P	Au-Sn	B-U
Ag-Mo	Al-Bi	Al-P	As-Pb	Au-Te	B-V
Ag-Nb	Al-C	Al-Pd	As-Pt	Au-Ti	B-W
Ag-Nd	Al-Ca	Al-Pb	As-Sb	Au-Tl	B-Zr
Ag-Ni	Al-Ce	Al-Pr	Au-B	Au-Tm	Ba-Cu
Ag-Os	Al-Co	Al-Pt	Au-Bi	Au-Zn	Ba-Eu

Ba-Mg	C-Cu	Ca-Li	Ce-V	Cr-Cu	Cu-Er
Ba-Ru	C-Fe	Ca-Mg	Ce-Y	Cr-Fe	Cu-Eu
Ba-Sr	C-Hf	Ca-Pb	Co-Cr	Cr-Ga	Cu-Fe
Ba-Y	C-Ir	Ca-Ru	Co-Cu	Cr-Ge	Cu-Ga
Bi-Ce	C-Li	Ca-Sc	Co-Dy	Cr-Hf	Cu-Ge
Bi-Cu	C-Mg	Ca-Si	Co-Er	Cr-La	Cu-H
Bi-Ga	C-Mn	Ca-Sr	Co-Fe	Cr-Mg	Cu-Hf
Bi-Gd	C-Mo	Ca-Zn	Co-Ga	Cr-Mn	Cu-Ho
Bi-Ge	C-N	Cd-Ga	Co-Gd	Cr-Mo	Cu-In
Bi-Hg	C-Nb	Cd-Gd	Co-Ge	Cr-N	Cu-Ir
Bi-Ho	C-Ni	Cd-Ge	Co-Hf	Cr-Nb	Cu-La
Bi-In	C-Os	Cd-Hg	Co-In	Cr-Ni	Cu-Li
Bi-K	C-P	Cd-In	Co-Mn	Cr-P	Cu-Mg
Bi-Lu	C-Pb	Cd-Na	Co-Mo	Cr-Pd	Cu-Mn
Bi-Nd	C-Pd	Cd-Pb	Co-N	Cr-Pt	Cu-Mo
Bi-Ni	C-Pt	Cd-Sb	Co-Nb	Cr-Ru	Cu-Nb
Bi-Pb	C-Pu	Cd-Te	Co-Ni	Cr-Sc	Cu-Nd
Bi-Pd	C-Rh	Cd-Y	Co-Pd	Cr-Si	Cu-Ni
Bi-Sb	C-Ru	Cd-Zn	Co-Pt	Cr-Sn	Cu-P
Bi-Se	C-Si	Ce-Co	Co-Sb	Cr-Ta	Cu-Pb
Bi-Si	C-Ta	Ce-Cr	Co-Si	Cr-Ti	Cu-Pd
Bi-Sn	C-Ti	Ce-Cu	Co-Sm	Cr-V	Cu-Pr
Bi-Tb	C-U	Ce-Fe	Co-Sn	Cr-W	Cu-Pt
Bi-Tl	C-V	Ce-La	Co-Ta	Cr-Y	Cu-Rh
Bi-Tm	C-W	Ce-Mg	Co-Ti	Cr-Zn	Cu-Sb
Bi-Y	C-Zn	Ce-Mn	Co-V	Cr-Zr	Cu-Sc
Bi-Zn	C-Zr	Ce-Mo	Co-W	Cs-In	Cu-Si
C-Ce	Ca-Cu	Ce-Ni	Co-Y	Cs-K	Cu-Sm
C-Co	Ca-Ga	Ce-Sb	Co-Zn	Cs-Na	Cu-Sn
C-Cr	Ca-H	Ce-Si	Co-Zr	Cs-Rb	Cu-Sr

Cu-Ti	Fe-Mn	Ga-N	Ge-Sr	In-La	Li-Pb
Cu-Tl	Fe-Mo	Ga-Ni	Ge-Te	In-Ni	Li-Sc
Cu-Tm	Fe-N	Ga-P	Ge-Ti	In-P	Li-Si
Cu-V	Fe-Nb	Ga-Pb	Ge-Tl	In-Pb	Li-Sn
Cu-W	Fe-Nd	Ga-Pt	Ge-V	In-Pd	Li-Sr
Cu-Y	Fe-Ni	Ga-Sb	Ge-Zn	In-Pt	Li-Zr
Cu-Yb	Fe-P	Ga-Sc	H-La	In-Sb	Lu-Sb
Cu-Zn	Fe-Pb	Ga-Si	H-Li	In-Se	Mg-Mn
Cu-Zr	Fe-Pd	Ga-Sn	H-Nd	In-Si	Mg-Nd
Dy-Er	Fe-Pr	Ga-Ti	H-Ni	In-Sn	Mg-Ni
Dy-Fe	Fe-Ru	Ga-Zn	H-Pd	In-Yb	Mg-Pr
Dy-Ho	Fe-Sb	Gd-Ge	Hf-Mo	In-Zn	Mg-Ru
Dy-Mg	Fe-Sc	Gd-Li	Hf-Nb	Ir-Ni	Mg-Sc
Dy-Mn	Fe-Si	Gd-Mg	Hf-Ni	Ir-Pd	Mg-Si
Dy-Ni	Fe-Sm	Gd-Mn	Hf-Si	Ir-Pt	Mg-Sm
Dy-Tb	Fe-Sn	Gd-Mo	Hf-Sn	Ir-Rh	Mg-Sn
Er-Ho	Fe-Sr	Gd-Ni	Hf-Ta	Ir-Ru	Mg-Sr
Er-Mg	Fe-Ta	Gd-Sc	Hf-Ti	Ir-Zr	Mg-Tb
Er-Ni	Fe-Tb	Gd-Si	Hf-V	K-Na	Mg-Ti
Er-Sb	Fe-Ti	Gd-Zr	Hf-W	K-Rb	Mg-Tm
Er-Tb	Fe-U	Ge-In	Hf-Zr	K-Zr	Mg-V
Er-V	Fe-V	Ge-Mg	Hg-Mg	La-Mg	Mg-Y
Er-Y	Fe-W	Ge-Na	Hg-Pb	La-Ni	Mg-Yb
Eu-In	Fe-Y	Ge-Ni	Hg-Sn	La-Sb	Mg-Zn
Eu-Mg	Fe-Zn	Ge-Pb	Hg-Zn	La-Sc	Mg-Zr
Eu-Pd	Fe-Zr	Ge-Pt	Ho-Mg	La-Sn	Mn-Mo
Eu-Sn	Ga-Ge	Ge-Ru	Ho-Mn	La-V	Mn-N
Fe-Gd	Ga-Hg	Ge-Sb	Ho-Mo	Li-Mg	Mn-Nb
Fe-La	Ga-In	Ge-Si	Ho-Tb	Li-N	Mn-P
Fe-Mg	Ga-Mg	Ge-Sn	Ho-V	Li-Na	Mn-Pb

Mn-Pr	N-U	Ni-Sm	Pd-Sn	Sc-Y	Ti-Zr
Mn-Sc	N-V	Ni-Sn	Pd-Tb	Sc-Zr	Tl-Zn
Mn-Si	N-W	Ni-Sr	Pd-Zn	Se-Te	U-V
Mn-Sm	N-Zr	Ni-Ta	Pd-Zr	Si-Sn	U-Zr
Mn-Sn	Na-Rb	Ni-Th	Pr-Sb	Si-Sr	V-W
Mn-Sr	Na-Sr	Ni-Ti	Pt-Rh	Si-Ta	V-Y
Mn-Ti	Na-Zn	Ni-V	Pt-Ru	Si-Ti	V-Zr
Mn-V	Na-Zr	Ni-W	Pt-Sb	Si-U	W-Zr
Mn-W	Nb-Ni	Ni-Y	Pt-Si	Si-V	Y-Zr
Mn-Y	Nb-Si	Ni-Zn	Pt-Sn	Si-W	Zn-Zr
Mn-Zn	Nb-Sn	Ni-Zr	Pt-Ta	Si-Y	
Mn-Zr	Nb-Ta	Os-Si	Pt-Ti	Si-Yb	
Mo-N	Nb-Ti	P-Sb	Pt-V	Si-Zn	
Mo-Nb	Nb-V	P-Si	Re-Si	Si-Zr	
Mo-Ni	Nb-W	P-Sn	Re-Ti	Sm-Sn	
Mo-P	Nb-Y	Pb-Pd	Ru-Si	Sm-Zn	
Mo-Pd	Nb-Zr	Pb-Pt	Ru-Sn	Sn-Ti	
Mo-Sc	Nd-Ni	Pb-Sb	Ru-Zr	Sn-V	
Mo-Si	Nd-Pr	Pb-Si	Sb-Si	Sn-Y	
Mo-Ta	Nd-Sb	Pb-Sn	Sb-Sm	Sn-Zn	
Mo-Ti	Nd-Sc	Pb-Sr	Sb-Sn	Sn-Zr	
Mo-V	Nd-Y	Pb-Te	Sb-Tb	Sr-Zn	
Mo-W	Nd-Zn	Pb-Tl	Sb-Tm	Ta-Ti	
Mo-Y	Ni-P	Pb-Zn	Sb-Y	Ta-V	
Mo-Zr	Ni-Pb	Pb-Zr	Sb-Zn	Ta-W	
N-Nb	Ni-Pd	Pd-Rh	Sc-Si	Ta-Zr	
N-Ni	Ni-Ru	Pd-Ru	Sc-Sr	Th-Zn	
N-Si	Ni-Sb	Pd-Sc	Sc-Th	Ti-V	
N-Ta	Ni-Sc	Pd-Si	Sc-V	Ti-W	
N-Ti	Ni-Si	Pd-Sm	Sc-W	Ti-Zn	

SSOL7 Assessed Ternary Systems

Ag-Au-Bi
Ag-Au-Sb
Ag-Bi-Sn
Ag-Cu-Ni
Ag-Cu-Pb
Ag-Cu-Sn
Ag-In-Sn
Ag-Ni-Sn
Al-C-Si
Al-C-V
Al-Ca-Si
Al-Cu-Li
Al-Cu-Mg
Al-Cu-Si
Al-Cu-Zn
Al-Er-Mg
Al-Fe-Mn
Al-Fe-Si
Al-Ga-In
Al-Ga-Sn
Al-Mg-Mn
Al-Mg-Si
Al-Mg-Zn
Al-Mn-Si
Al-Si-Zn
Al-Sn-Zn
As-Cu-Ni

As-Ga-In
Au-Bi-Sb
Au-In-Pb
Au-In-Sb
Au-In-Sn
Au-Ni-Sn
B-Fe-Nd
Bi-Cu-Ga
Bi-Ga-Zn
Bi-In-Pb
Bi-In-Sn
Bi-Sb-Sn
Bi-Sn-Zn
C-Co-Cr
C-Co-Fe
C-Co-Ni
C-Co-W
C-Cr-Fe
C-Cr-Mn
C-Cr-Mo
C-Cr-N
C-Cr-Ni
C-Cr-Si
C-Cr-Ti
C-Cr-V
C-Cr-W
C-Cu-Fe

C-Fe-Mn
C-Fe-Mo
C-Fe-N
C-Fe-Nb
C-Fe-Ni
C-Fe-Si
C-Fe-Ti
C-Fe-V
C-Fe-W
C-Mn-Si
C-Mn-V
C-Mo-N
C-Mo-Ti
C-Mo-V
C-Mo-W
C-N-Nb
C-N-Ti
C-Ni-Si
C-Ni-Ti
C-Ni-W
C-Si-Ti
C-Ti-W
C-V-W
Cd-Ga-In
Co-Cr-W
Co-Fe-N
Co-Fe-W

Co-Ni-W
Cr-Fe-Mn
Cr-Fe-Mo
Cr-Fe-N
Cr-Fe-Ni
Cr-Fe-P
Cr-Fe-Ti
Cr-Fe-V
Cr-Fe-W
Cr-Mn-N
Cr-Mn-Ti
Cr-Mo-N
Cr-Mo-Ni
Cr-Mo-W
Cr-N-Ni
Cr-N-Ti
Cr-N-V
Cr-Ni-W
Cr-Ni-Ta
Cr-Ni-W
Cr-Si-Ti
Cr-Ti-V
Cu-Fe-Ni
Cu-Fe-P
Cu-H-Pd
Cu-In-Sn
Cu-Mg-Si

Cu-Mg-Zn
Cu-Ni-Pb
Cu-Ni-Sn
Dy-Fe-Tb
Fe-Mn-N
Fe-Mn-Nb
Fe-Mn-Si
Fe-Mn-V
Fe-Mo-N
Fe-Mo-Ni
Fe-Mo-P
Fe-Mo-V
Fe-Mo-W
Fe-N-Nb
Fe-N-Ni
Fe-N-Ti
Fe-N-V
Fe-N-W
Fe-Ni-P
Fe-Ni-W
Fe-Si-Zn
Fe-Ti-W
Fe-U-Zr
Ga-In-Sb
Ge-Ru-Si
Ge-Ru-Sn
H-Nd-Ni

In-Sb-Sn
In-Sn-Zn
Mo-N-Ni
Mo-Ni-W
N-Si-Ti
Pb-Pd-Sn

SSOL7 Assessed Quaternary Systems

C-Co-Cr-W	C-Co-Fe-Ni	C-Co-Fe-Ni-W	C-Co-Fe-W
C-Co-Ni-W	C-Cr-Fe-Mn	C-Cr-Fe-Mo	C-Cr-Fe-Ni
C-Cr-Fe-Si	C-Cr-Fe-V	C-Cr-Fe-W	C-Cr-Mo-V
C-Fe-Mn-V	C-Fe-Mo-V	C-Fe-Mo-W	C-Fe-Ni-W
C-Fe-V-W	Co-Fe-Ni-W	Cr-Fe-Mn-N	Cr-Fe-N-Ni

SSOL7 Phase Models

This information is contained on the following pages.

Phase Name	Number of Sublattices	Stoichiometry					Occupancy				
		SL1	SL2	SL3	SL4	SL5	SL1	SL2	SL3	SL4	SL5
GAS:G	1	1					AL1 AL2 C C2 C3 C4 C5 C60 CA CA2 CAH CD CU CU2 CUH H H2 HLI LA LI L2 MG MG2 ND NI1 NI2 N1 N2 N3 O2 P1 P2 P3 P4 TE TE2 TE3 TE4 TE5 TE6 TE7				
LIQUID:L	1	1					AG AL AM AS AU B BA BE BI C CA CD CE CO CR CS CU DY ER EU FE GA GD GE H HF HG HO IN IR K LA LI LU MG MN MO N NI1 NA NB ND NI NP O OS P PA PB PD PR PT PU RB RE RH RU S SB SC SE SI SM SN SR TA TB TC TE TH TI TL TL TM U V W Y YB ZN ZR Bi2SE3 CDTE MG2SN GETE IN2SE3 CR3GE1 AG2TE PBTE PTSN LASN Li2C2 LIH Li4PB				
FCC_A1	2	1	1				AG% AL% AM AS AU% BA BE BI CA% CD CE% CO% CR CS CU% DY ER EU FE% GA GD GE HF HG HG HO IN IR% K LA LI MG MN MO NA NB ND NI% O OS P PB% PD% PR PT% PU RB RE RH% RU S SB SC SI SM SN SR TA TB TC TH TI TL U V W Y YB ZN ZR	VA% C H N B			
FCC_L12	3	0,75	0,25		1		AG% AL% AM AS AU% BA BE BI CA% CD CE% CO% CR CS CU% DY ER EU FE% GA GD GE HF HG HO IN IR% K LA LI MG MN MO NA NB ND NI% O OS P PB% PD% PR PT% PU RB RE RH% RU S SB SC SI SM SN SR TA TB TC TH TI TL U V W Y YB ZN	AG% AL% AM AS AU% BA BE BI CA% CD CE% CO% CR CS CU% DY ER FE% GA GD GE HF HG			
FCC_L10	2	0,5	0,5				ZR MN% NI	HO IN IR% K LA LI MG MN MO NA NB ND NI% O OS P PB% PD% PR PT% PU RB RE RH% RU S SB SC SI SM SN SR TA TB TC TH TI TL U V W Y YB ZN	ZR MN NI%	B C N VA%	
FCC_4SL	5	0,25	0,25	0,25	0,25	1	AL AU CU CO IR PT V	AL AU CU CO IR PT V	AL AU CU CO IR PT V	AL AU CU CO IR PT V	AL AU CU CO IR PT V
BCC_A2	2	1	3				AG AL AM AS AU BA% BE BI CA CD CE CO CR% CS% CU DY ER EU FE% GA GD GE HF HO IN IR K% LA LI% MG MN MO% NA% NB% ND NI NP O OS P PA PB PD PR PT PU RB% RE RH RU S SB SC SI SM SN SR TA% TB TC TH TI% TL TM U V% W% Y YB ZN ZR	B C H N VA%			
BCC_B2	3	0,5	0,5		3		AG AL AM AS AU BA% BE BI CA CD CE CO CR% CS% CU DY ER EU FE% GA GD GE HF HO IN IR K% LA LI% MG MN MO% NA% NB% ND NI NP O OS P PA PB PD PR PT PU RB% RE RH RU S SB SC SI SM SN SR TA% TB TC TH TI% TL TM U V% W% Y YB ZN ZR	AG AL AM AS AU BA% BE BI CA CD CE CO CR% CS% CU DY ER EU FE% GA GD GE HF HO IN IR K% LA LI% MG MN MO% NA% NB% ND NI NP O OS P PA PB PD PR PT PU RB% RE RH RU S SB SC SI SM SN SR TA% TB TC TH TI% TL TM U V% W% Y YB ZN ZR	B C H N VA%		
B2	2	1	1				AL CO IN NI PD	VA CO NI PD			
A2_BCC	2	1	3				AL CO HF IR VA	VA			
B2_BCC	3	0,5	0,5		3		AL CO% HF IR VA	AL CO HF% IR VA	VA		
HCP_A3	2	1	0,5				AG% AL AS AU BA BE% BI CA CD% CE CO% CR CS CU DY% ER% EU FE GA GD% GE HF% HG HO% IN IR K LA LI LU% MG% MN MO NA NB ND NI OS% PB PD PR PT RB RE% RH RU% SB SC SI SM SN SR TA TB% TC% TH TI% TL% TM% U V W Y YB ZN% ZR%	B C N VA%			
HCP_ORD	5	0,25	0,25	0,25	0,25	0,5	CO V	CO V	CO V	CO V	VA
HCP_ZN	2	1	0,5				AG AL AU BI CD CR CU FE GA HG IN MG PB PD SI SN ZN%	VA			
DHCP	2	1	2				AG AL AM% AU BI CE GA IN LA% MG MN ND% NI PR% SC SN Y	H VA			
DIAMOND_A4	1	1					AL B BI C GA GE% P PD RU SI% SN SR TI ZN				

Phase Name	Number of Sublattices	Stoichiometry					Occupancy				
		SL1	SL2	SL3	SL4	SL5	SL1	SL2	SL3	SL4	SL5
BCT_A5	1	1									
TETRAGONAL_A6	1	1									
TET_ALPHA1	1	1									
TETRAGONAL_U	1	1									
RHOMBOHEDRAL_A7	1	1									
HEXAGONAL_A8	1	1									
RHOMBO_A10	1	1									
BETA_RHOMBO_B	1	1									
ALPHA_RHOMBO_B	1	1									
BETA_RHOMB_BCSI	2	93	12								
CHI_A12	3	24	10	24							
CBCC_A12	2	1	1								
CUB_A13	2	1	1								
CUB_A15	2	3	1								
ORTHORHOMBIC_A20	1	1									
SIGMA	3	8	4	18							
HIGH_SIGMA	3	8	4	18							
MU_PHASE	3	7	2	4							
MU_D85	4	1	4	2	6						
P_PHASE	3	24	20	12							
R_PHASE	3	27	14	12							
ZINCLENDE_B3	2	0,5	0,5								
GRAPHITE	1	1									
RED_P	1	1									
WHITE_P	1	1									
MONOCLINIC	1	1									
ORTHORHOMBIC_S	1	1									
ORTHORHOMBIC_GA	1	1									
ORTHORHOMBIC_AC	1	1									
TETRAG_A	1	1									
BCT_AA	1	1									
ALPHA_PU	1	1									
BETA_PU	1	1									
GAMMA_PU	1	1									
RHOMBO_C19	1	1									
OMEGA_ZR	1	1									
LAVES_C14	2	2	1								
C14_LAVES	2	2	1								
LAVES_C15	2	2	1								
LAVES_C36	2	2	1								
CEMENTITE	2	3	1								
KSI_CARBIDE	2	3	1								
M23C6	3	20	3	6							
M7C3	2	7	3								

Phase Name	Number of Sublattices	Stoichiometry					Occupancy				
		SL1	SL2	SL3	SL4	SL5	SL1	SL2	SL3	SL4	SL5
M6C	4	2	2	2	1		CO FE NI CR FE MN MO V W	MO W	CO CR FE MO NI V W	C	
M3C2	2	3	2				FE MN V	C			
V3C2	2	3	2				FE MN V	C			
M5C2	2	5	2				CO	W			
M12C	3	6	6	1			MO W%	C N			
MC_SHP	2	1	1				MO% V W	VAC%			
MC_ETA	2	1	1				AL SI	C			
AL4C3	2	4	3				AL	SI		C	
AL8SiC7	3	8	1	7			AL	SI		C	
AL4SiC4	3	4	1	4			AL	SI		C	
CR2VC2	3	2	1	2			CR	V		C	
FE8Si2C	3	8	2	1			FE	SI		C	
SIC	2	1	1				SI	C			
ALN	2	1	1				AL	N			
M4N	2	4	1				CR CO FE MN NI	VACN			
FECN_CHI	2	5	2				FE	C N			
PI_PHASE	3	12,8	7,2	4			CR	FE NI		N	
T12N	2	2	1				TI	C N			
B4C	2	1	1				B11C1 B12	B2 C1B2 C2B B1C2 B2C1			
BN_HP4	2	1	1				B	N			
MN6N4	2	6	4				MN	N			
MN6N5	2	6	5				MN	N			
EPSILON_TAN	1	1					TA1N				
T13N2	1	1					TI.71N.29				
T14N3	1	1					TI.685N.315				
ALB2	2	1	2				AL	B			
ALB12_ALPHA	2	1	12				AL	B			
BAB6	2	1	6				BA	B			
CAB6	2	1	6				CA	B			
SRB6	2	1	6				SR	B			
CR2B_ORTH	2	0,667	0,333				CR	B			
CR3B4	2	0,429	0,571				CR	B			
CR5B3	2	0,625	0,375				CR	B			
CRB	2	0,5	0,5				CR	B			
CRB2	2	0,333	0,667				CR	B			
CRB4	2	0,2	0,8				CR	B			
FE2B	1	1					FE2B				
FEB	1	1					FE1B				
FENDB_T1	1	1					FE14ND2B1				
FENDB_T2	1	1					ND1.11FE4B4				
FENDB_T3	1	1					FE2ND5B6				
BM	2	1	1				B	HF TI			
B2M	2	2	1				B	HF TI			
M2B_TETR	2	0,667	0,333				MO NI	B			
B4M3	2	4	3				B	HF TI			
MOB	2	0,5	0,5				MO	B			
MOB4	2	0,2	0,8				MO	B			
MOB2	2	0,38	0,62				MO	B			
MO2B5	2	0,32	0,68				MO	B			
NB3B2_D5A	2	3	2				NB	B			
NBB_B33	2	1	1				NB	B%NB			
NB5B6	2	5	6				NB	B			
NB3B4_D7B	2	3	4				NB	B			
NB2B3	2	2	3				NB	B			

Phase Name	Number of Sublattices	Stoichiometry					Occupancy				
		SL1	SL2	SL3	SL4	SL5	SL1	SL2	SL3	SL4	SL5
NBB2_C32	2	1	2				B NB%				
NDB4	1	1					ND1B4				
NDB6	1	1					ND1B6				
NDB66	1	1					ND1B66				
ND2B5	1	1					ND2B5				
ND2Y_C19	2	2	1				ND% Y				
NI3B	2	0,75	0,25				NI				
NI4B3_O	2	0,586	0,414				NI				
NI4B3_M	2	0,564	0,436				NI				
NIB	2	0,5	0,5				NI				
SIB3	3	6	2	6			B		SI		
SIB6	3	210	23	48			B		SI		
B_NSI	3	61	1	8			B		SI		
VB	2	0,5	0,5				V		B		
VB2	2	0,333	0,667				V		B		
V2B3	2	0,4	0,6				V		B		
V3B2	2	0,6	0,4				V		B		
V3B4	2	0,4286	0,5714				V		B		
WB_ALPHA	2	1	1				W		B VA		
WB_BETA	2	1	1				W		B VA		
WB3	1	1					W2B9				
W2B	1	1					W2B1				
W2B5	2	2	5				W		B VA		
ASP	1	1					AS P				
CU3P	2	3	1				CU FE		P		
FEP	2	1	1				FE		P		
M2P	2	2	1				CR FE MO NI		P		
M3P	2	3	1				CR FE CU MO NI		P		
MNP	1	1					MN1P				
MNP3	1	1					MN1P3				
MN3P	1	1					MN3P				
MN2P	1	1					MN2P				
MOP	2	1	1				MO		P		
NI5P2_H	2	5	2				NI		P		
NI5P2_L	2	5	2				CU NI		P		
NI6P5	2	6	5				NI		P		
NI12P5	2	12	5				NI		P		
PSI	2	1	1				P		SI		
AGBA	2	1	1				AG		BA		
AG2BA	2	2	1				AG		BA		
AG2BA3	2	2	3				AG		BA		
AG5BA	2	5	1				AG		BA		
AG3BE8	2	2,97	8,03				AG		BE		
AGCA	2	1	1				AG		CA		
AGCA3	2	1	3				AG		CA		
AG2CA	2	2	1				AG		CA		
AG3CA5	2	3	5				AG		CA		
AG7CA2	2	7	2				AG		CA		
AG9CA2	2	9	2				AG		CA		
AGCD	2	1	1				AG		CD		
AG2CD3	2	2	3				AG		CD		
AGCD_ETA	1	1					AG CD				
AGCE	2	1	1				AG		CE		
AG2CE	2	2	1				AG		CE		
AG4CE	2	4	1				AG		CE		

Phase Name	Number of Sublattices	Stoichiometry					Occupancy				
		SL1	SL2	SL3	SL4	SL5	SL1	SL2	SL3	SL4	SL5
AG51CE14	2	51	14				AG	CE			
AG51DY14	2	0,7846	0,2154				AG	DY			
AG2DY	2	0,6667	0,3333				AG	DY			
AGDY	2	0,5	0,5				AG	DY			
AG51ER14	2	0,7846	0,2154				AG	ER			
AG2ER	2	0,6667	0,3333				AG	ER			
AGER	2	0,5	0,5				AG	ER			
AG2GA	2	2	1				AG	AG GA VA			
AG3GA2_B2	2	3	2				AG	GA			
AG51GD14	2	51	14				AG	GD			
AG2GD_C11B	2	2	1				AG	GD			
AGGD_B2	2	1	1				AG	GD			
AGIN2	2	0,33	0,67				AG	IN			
AGMG3	2	0,25	0,75				AG	MG			
AG3MG	2	0,75	0,25				AG	MG			
AGND	2	0,5	0,5				AG	ND			
AG2ND_BETA	2	0,667	0,333				AG	ND			
AG2ND_ALPHA	2	0,667	0,333				AG	ND			
AG51ND14	2	0,785	0,215				AG	ND			
AGSB_ORTHO	2	0,75	0,25				AG AU SB		AG AU BI SB SN		
AGSC	2	1	1				AG		SC		
AG2SC	2	2	1				AG		SC		
AG4SC	2	4	1				AG		SC		
AGSR	2	1	1				AG		SR		
AG2SR	2	2	1				AG		SR		
AG2SR3	2	2	3				AG		SR		
AG4SR	2	4	1				AG		SR		
AG5SR	2	5	1				AG		SR		
AG2TE	2	2	1				AG,PB		TE		
AG5TE3	2	31	19				AG		TE		
AG65STE345	2	0,655	0,345				AG		TE		
AGTI2	2	1	2				AG		TI		
AGTI	2	1	1				AG TI		AG TI		
AG51Y14	2	51	14				AG		Y		
AG2Y_C11B	2	2	1				AG		Y		
AGY_B2	2	1	1				AG		Y		
AGZN_GAMMA	4	2	2	3	6		AG ZN		AG ZN		AG
AGZN_ZETA	2	1	2				ZN		AG ZN		ZN
AGZR2	2	0,33333	0,66667				AG		ZR		
AGZR	2	0,5	0,5				AG		ZR		
ALM_D019	2	3	1				AL MO NB TA TI V W		AL MO NB TA TI V W		
AL3M_D022	2	3	1				AL MO TI		MO NB TA TI V		
ALAU	1	1					AL1AU				
ALAU2	1	1					AL1AU2				
ALAU4	1	1					AL1AU4				
AL2AU	1	1					AL2AU				
AL2AU5	1	1					AL2AU5				
AL4CA_D13	2	4	1				AL		CA		
AL2CA_C15	2	2	1				AL		CA		
ALCA	2	1	1				AL		CA		
AL3CA8	2	3	8				AL		CA		
AL2CAS12	3	2	1	2			AL		CA		SI
ALCE_AMORPHOUS	1	1					AL CE				
AL_CEND	2	1	1				AL		CE ND		
AL_CEND3_H	2	1	3				AL		CE		

Phase Name	Number of Sublattices	Stoichiometry					Occupancy				
		SL1	SL2	SL3	SL4	SL5	SL1	SL2	SL3	SL4	SL5
AL_CEND3_L	2	1	3				AL	CE ND			
AL2_CEND	2	2	1				AL	CE			
AL3_CEND	2	3	1				AL	CE ND			
AL11_CEND3_H	2	11	3				AL	CE ND			
AL11_CEND3_L	2	11	3				AL	CE ND			
AL5CO2	2	5	2				AL	CO			
AL3CO	2	3	1				AL	CO			
AL13CO4	2	13	4				AL	CO			
AL9CO2	2	9	2				AL	CO			
AL45CR7	2	45	7				AL	CR			
AL5CR	2	5	1				AL	CR			
AL4CR	2	4	1				AL VA	CR			
AL8CR5_ALPHA	4	12	5	5	4		AL	CR	AL CR	AL CR	
AL8CR5_BETA	4	2	3	2	6		AL CR	AL CR	CR	AL	
ALCR2_C11B	2	1	2				AL% CR	AL CR%			
ALCU_ETA	2	1	1				CU AL	CUZN			
ALCU_EPSILON	2	1	1				AL CUZN	CU			
ALCU_THETA	2	2	1				AL	AL CU			
ALCU_DELTA	2	2	3				AL ZN	CU			
ALCU_ZETA	2	9	11				AL ZN	CU			
ALCULI_R	3	0,55	0,117	0,333			AL	CU	LI		
ALCULI_T1	3	0,5	0,25	0,25			AL	CU	LI		
ALCULI_T2	3	0,57	0,11	0,32			AL	CU	LI		
ALCULI_TB	3	0,6	0,32	0,08			AL	CU	LI		
ALCUMG_QPHASE	3	7	3	6			AL	CU	MG		
ALCUMG_SPHASE	3	2	1	1			AL	CU	MG		
ALCUMG_VPHASE	3	5	6	2			AL	CU	MG		
ALCUZN_GAMMA_H	4	2	2	3	6		CU	AL,CU	CU	AL,CU	
ALCUZN_TAU	4	1	4	4	1		AL,CU	AL	CU	ZN	
AL3DY_D024	2	3	1				AL	DY			
ALDY	2	1	1				AL	DY			
AL2DY3	2	2	3				AL	DY			
ALDY2	2	1	2				AL	DY			
ALER	2	1	1				AL MG	ER			
ALER2	2	1	2				AL	ER			
AL2ER3	2	2	3				AL	ER			
ALERMG_T	3	0,6667	0,1	0,2333			AL	ER	MG		
AL2FE	2	2	1				AL	FE MN			
AL5FE2	2	5	2				AL	FE MN			
AL5FE4	1	1					AL FE MN				
AL13FE4	3	0,6275	0,235	0,1375			AL	FE MN	AL VA SI		
ALFESI_ALPHA	4	0,6612	0,19	0,0496	0,0992		AL	FE	SI	AL SI	
ALFESI_BETA	3	14	3	3			AL	FE	SI		
ALFESI_GAMMA	3	3	1	1			AL	FE	SI		
ALFESI_DELTA	3	0,55	0,15	0,3			AL	FE	SI		
ALFESI_TAU1	3	2	2	1			AL	FE	SI		
ALFESI_TAU3	3	2	1	1			AL	FE	SI		
AL3GD	2	3	1				AL	GD			
ALGD	2	1	1				AL	GD			
AL2GD3	2	2	3				AL	GD			
ALGD2	2	1	2				AL	GD			
AL3HF_D023	2	3	1				AL	HF			
AL3HF_D022	2	3	1				AL	HF			
AL2HF_C14	2	2	1				AL	HF			
AL3HF2	2	3	2				AL	HF			

Phase Name	Number of Sublattices	Stoichiometry					Occupancy				
		SL1	SL2	SL3	SL4	SL5	SL1	SL2	SL3	SL4	SL5
ALHF_B33	2	1	1				AL	HF			
AL3HF4	2	3	4				AL	HF			
AL2HF3	2	2	3				AL	HF			
ALHF2_C16	2	1	2				AL	HF			
HOAL3	2	3	1				AL	DY HO			
ALHO	2	1	1				AL	HO			
AL2HO3	2	2	3				AL	HO			
ALHO2	2	1	2				AL	HO			
AL9IR2	2	9	2				AL	IR			
AL45IR13	2	45	13				AL	IR			
AL13IR4	2	13	4				AL	IR			
AL28IR9	2	28	9				AL	IR			
AL3IR_D018	2	3	1				AL	IR			
AL5IR2	2	2,7	1				AL	IR			
ALLA	1	1					AL1LA				
ALLA3	1	1					AL1LA3				
AL2LA	1	1					AL2LA				
AL3LA	1	1					AL3LA				
AL11LA3D	1	1					AL11LA3				
AL11LA3F	1	1					AL11LA3				
AL53LA22	1	1					AL53LA22				
ALLI	2	1	1				AL LI MG	LI MG VA			
AL2LI3	2	2	3				AL	LI			
AL4L9	2	4	9				AL	LI			
ALMG_BETA	2	89	140				MG	AL ZN			
GAMMA_A12	3	5	12	12			ER MG	AL MG ZN	AL MG ZN		
ALMG_GAMMA1	3	5	12	12			DY HO MG	MG	MG		
ALMG_EPSILON	2	23	30				MG	AL ZN			
ALMG_DZETA	2	21	19				AL	MG			
AL12MG17	3	24	10	24			LI MG	AL LI MG	AL MG		
ALMGMN_T	3	18	3	2			AL	MG	MN		
ALMGZN_PHI	2	6	5				MG	AL ZN			
ALMGZN_TAU	4	26	6	48	1		MG	AL MG	AL CU MG ZN	AL	
AL4MN	2	4	1				AL	FE MN			
AL6MN	2	6	1				AL	FE MN			
AL8MN5_D810	3	12	4	10			AL SI	MN	AL FE MN		
AL11MN4	2	11	4				AL	FE MN			
AL12MN	2	12	1				AL	FE MN			
ALMNSI_ALPHA	4	16	4	1	2		AL	MN	SI	AL SI	
ALMNSI_DELTA	3	2	1	3			AL	MN	SI		
ALMNSI_BETA	4	15	1	4	6		AL	SI	AL SI	MN	
AL4MO	2	4	1				AL	MO			
AL5MO	2	5	1				AL	MO			
AL8MO3	2	8	3				AL	MO			
AL12MO	2	12	1				AL	MO			
AL63MO37	2	63	37				AL	MO			
ALNB2	3	0,533	0,333	0,134			AL NB	AL NB	NB		
ALNB3	2	0,75	0,25				AL NB	AL NB			
AL3NB	2	0,25	0,75				AL NB	AL NB			
ALND2	2	1	2				AL	ND			
AL3NI	2	3	1				AL	NI			
AL3NI2	3	3	2	1			AL	AL NI	VAN NI		
AL3NI5	2	3	5				AL	NI			
AL4PD	2	4	1				AL	PD			
AL3PD	2	3	1				AL	PD			

Phase Name	Number of Sublattices	Stoichiometry					Occupancy				
		SL1	SL2	SL3	SL4	SL5	SL1	SL2	SL3	SL4	SL5
AL21PD8	2	21	8				AL	PD			
AL3PD2_D513	2	3	2				AL% PD	AL PD%			
ALPD_B2	2	1	1				AL% PD	PD% VA			
AL3PD5	2	3	5				AL	PD			
AL2PD5	2	2	5				AL	AL PD%			
ALPD2_C37	2	1	2				AL% PD	AL PD%			
ALPR	2	1	1				AL	PR			
AL11PR3	2	11	3				AL	PR			
ALPR2	2	1	2				AL	PR			
ALPR3	2	1	3				AL	PR			
AL2PR	2	2	1				AL	PR			
AL3PR	2	3	1				AL	PR			
ALPT3	2	0,25	0,75				AL PT	AL PT			
AL21PT5	2	21	5				AL	PT			
AL21PT8	2	21	8				AL	PT			
AL2PT	2	2	1				AL	PT			
AL3PT2	2	3	2				AL	PT			
ALPT	2	1	1				AL	PT			
AL3PT5	2	3	5				AL	PT			
ALRU	2	1	1				AL	RU			
AL13RU4	2	13	4				AL	RU			
AL2RU	2	2	1				AL	RU			
AL3RU2	2	3	2				AL	RU			
AL6RU	2	6	1				AL	RU			
AL3SC	2	3	1				AL	SC			
AL2SC	2	2	1				AL	SC			
ALSC	2	1	1				AL	SC			
ALSC2	2	1	2				AL	SC			
AL11SM3_LT	2	11	3				AL	SM			
AL11SM3_LT	2	11	3				AL	SM			
ALSM	2	1	1				AL	SM			
ALSM2	2	1	2				AL	SM			
AL2SM	2	2	1				AL	SM			
AL3SM	2	3	1				AL	SM			
AL7SR8	2	7	8				AL	SR			
AL2SR	2	2	1				AL	SR			
AL4SR	2	4	1				AL	SR			
ALTA	2	1	1				AL	TA			
ALTA_SIGMA	3	10	4	16			AL CO TA V	TA V	AL CO TA V		
AL3TA	2	3	1				AL	TA			
AL3TA2	2	3	2				AL	TA			
AL7TA5	2	7	5				AL	TA			
AL69TA39	2	69	39				AL	TA			
AL7TH2	2	7	2				AL	TH			
AL3TH_D019	2	3	1				AL	TH			
AL2TH_C32	2	2	1				AL	TH			
AL3TH2	2	3	2				AL	TH			
ALTH_BF	2	1	1				AL	TH			
AL2TH3_D5A	2	2	3				AL	TH			
ALTH2_C16	2	1	2				AL	TH			
ALTI	2	1	1				AL MO NB TA TI VW	AL MO NB TA TI VW			
AL2TI	2	2	1				AL	TI			
AL11TI5	2	17	8				AL	TI			
AL45V7	2	45	7				AL	V			
AL8V5	4	6	2	3	2		AL	AL,V	AL,V	V	

Phase Name	Number of Sublattices	Stoichiometry					Occupancy				
		SL1	SL2	SL3	SL4	SL5	SL1	SL2	SL3	SL4	SL5
AL21V2	2	21	2				AL	V			
AL23V4	2	23	4				AL	V			
AL2W	2	2	1				AL	W			
AL4W	2	4	1				AL	W			
AL5W	2	5	1				AL	W			
AL7W3	2	7	3				AL	W			
AL12W	2	12	1				AL	W			
AL77W23	2	77	23				AL	W			
ALY_BF	2	1	1				AL	Y			
ALY2_C23	2	1	2				AL	Y			
AL2Y3	2	2	3				AL	Y			
AL3Y_BETA	2	3	1				AL	Y			
AL3Y_D019	2	3	1				AL	Y			
AL3Y5	2	3	5				AL	Y			
ALZR	2	1	1				AL	ZR			
ALZR2	2	1	2				AL	ZR			
ALZR3	2	1	3				AL	ZR			
AL2ZR	2	2	1				AL	ZR			
AL2ZR3	2	2	3				AL	ZR			
AL3ZR	2	3	1				AL	ZR			
AL3ZR2	2	3	2				AL	ZR			
AL3ZR5	2	3	5				AL	ZR			
AL4ZR5	2	4	5				AL	ZR			
ASCUNI	3	0,334	0,333	0,333			AS	CU	NI		
AS2GE	2	0,6666	0,3333				AS	GE			
ASGE	2	0,5	0,5				AS	GE			
ASNI	2	1	1				AS	NI			
AS2NI	2	2	1				AS	NI			
AS2NI5	2	2	5				AS	NI			
AS8NI11	2	8	11				AS	NI			
AS2PT	2	2	1				AS	PT			
AU2BI_C15	2	2	1				AG, AU	BI			
AU4ER_D1A	2	4	1				AU	ER			
AU3ER_D0A	2	3	1				AU	ER			
AU2ER_C11B	2	2	1				AU	ER			
AU10ER7	2	10	7				AU	ER			
AUER_B33	2	1	1				AU	ER			
AUER_B2	2	1	1				AU	ER			
AUER2_C37	2	1	2				AU	ER			
AU7GA2_HT	2	0,7895	0,2105				AU	GA			
AU7GA2_LT	2	7	2				AU	GA			
AU7GA3	2	7	3				AU	GA			
AUGA_B31	2	1	1				AU	GA			
AUGA2_C1	2	1	2				AU	GA			
AU5HF	2	5	1				AU	AU HF			
AU4HF	2	4	1				AU	HF			
AU3HF	2	3	1				AU	HF			
AU2HF	2	2	1				AU	AU HF			
AU10HF7	2	10	7				AU	HF			
AUHF_ALPHA	2	1	1				AU	AU HF			
AUHF_BETA	2	1	1				AU	AU HF			
AUHF2	2	1	2				AU	HF			
AU6HO	2	6	1				AU	HO			
AU4HO_D1A	2	4	1				AU	HO			
AU51HO14	2	51	14				AU	HO			

Phase Name	Number of Sublattices	Stoichiometry					Occupancy				
		SL1	SL2	SL3	SL4	SL5	SL1	SL2	SL3	SL4	SL5
AU3HO_D0A	2	3	1				AU	HO			
AU2HO_C11B	2	2	1				AU	HO			
AU10HO7	2	10	7				AU	HO			
AUHO_B33	2	1	1				AU	HO			
AUHO_B2	2	1	1				AU	HO			
AUHO2_C37	2	1	2				AU	HO			
AUIN	2	0,5	0,5				AU	IN, SB, SN			
AUIN2	2	0,3333	0,6667				AU	IN, SB, SN			
AU3IN	2	3	1				AU	IN			
AU7IN3	2	7	3				AU	IN			
AUIN_BETA	2	7,065	1,935				AU	IN			
AUIN_GAMMA	3	0,69231	0,23077	0,07692			AU	AU, IN			
AUIN_PSI	3	0,5	0,33333	0,16667			AU	AU, IN			
AUIN_BETAP	2	14	4				AU	IN			
AU4IN3SN3	3	0,4	0,3	0,3			AU	IN%, SN			
AU6LA	2	6	1				AU	LA			
AU51LA14	2	51	14				AU	LA			
AU2LA	2	2	1				AU	LA			
AULA_B27	2	1	1				AU	LA			
AULA_B33	2	1	1				AU	LA			
AULA2_C37	2	1	2				AU	LA			
AUNI2SN4	3	0,143	0,286	0,571			AU	NI			SN
AUPB2	2	1	2				AU	PB			
AUPB3	2	1	3				AU	PB			
AU2PB	2	2	1				AU	PB			
AU6PR	2	6	1				AU	PR			
AU51PR14	2	51	14				AU	PR			
AU36PR17	2	36	17				AU	PR			
AU2PR	2	2	1				AU	PR			
AU4PR3	2	4	3				AU	PR			
AUPR_ALPHA	2	1	1				AU	PR			
AUPR_BETA	2	1	1				AU	PR			
AUPR_GAMMA	2	1	1				AU	PR			
AUPR2	2	1	2				AU	PR			
AUSB2	2	0,333333	0,666667				AG AU	BI IN SB			
AUSN	2	0,5	0,5				AU NI	IN SN			
AUSN2	2	0,333333	0,666667				AU	SN			
AUSN4	2	0,2	0,8				AU NI	IN SN			
AU5SN	2	0,84	0,16				AU	SN			
AUTE2	2	1	2				AU	TE			
TI3AU	2	3	1				TI	AU			
TI4AU	2	0,5	0,5				TI VA	AU TI			
TIAU2	2	1	2				TI	AU			
TIAU4	2	0,2	0,8				AU TI	AU			
AU4TM_D1A	2	4	1				AU	TM			
AU3TM_D0A	2	3	1				AU	TM			
AU2TM_C11B	2	2	1				AU	TM			
AU10TM7	2	10	7				AU	TM			
AUTM_B33	2	1	1				AU	TM			
AUTM_B2	2	1	1				AU	TM			
AUTM2_C37	2	1	2				AU	TM			
AU10ZR7	2	10	7				AU	ZR			
AUZR	2	1	1				AU	ZR			
AUZR2	2	1	2				AU	ZR			
AUZR3	2	1	3				AU	ZR			

Phase Name	Number of Sublattices	Stoichiometry					Occupancy				
		SL1	SL2	SL3	SL4	SL5	SL1	SL2	SL3	SL4	SL5
AU2ZR	2	2	2	1			AU	ZR			
AU2ZR3	2	2	2	3			AU	ZR			
AU3ZR	2	3	1				AU	ZR			
AU4ZR	2	4	1				AU	ZR			
AUZN_A3	3	0,64286	0,25	0,10714			AU	AU,ZN		ZN	
AUZN_A1	3	0,6	0,2	0,2			AU	AU,ZN		ZN	
AUZN_A2	2	0,75	0,25				AU	ZN			
AUZN_BETA	2	0,5	0,5				AU%,ZN	AU,ZN%			
AUZN_DELTA	2	0,44	0,56				AU	ZN			
AUZN_G2	2	0,25	0,75				AU	ZN			
AUZN_G3	3	0,12	0,16	0,72			AU	AU,ZN		ZN	
AUZN_E1	2	0,15	0,85				AU	ZN			
AU5ZN3	2	0,625	0,375				AU	ZN			
AUZN_BRASS	4	2	2	3	6		AU,ZN	AU	AU,ZN	ZN	
B2_INYB	2	0,5	0,5				IN,YB	IN,YB			
B27_COB	2	1	1				CO	B			
CO3B	2	3	1				CO	B			
C16_CO2B	2	2	1				CO	B			
B2MG	2	2	1				B	MG			
B4MG	2	4	1				B	MG			
B7MG	2	7	1				B	MG			
D2B_B12SC1	2	12	1				B	SC			
C32_B2SC1	2	2	1				B	SC			
MNB4	2	1	4				MN	B			
MNB2	2	1	2				MN	B			
MN3B4	2	3	4				MN	B			
MNB	2	1	1				MN	B			
MN2B_TET	2	2	1				MN	B			
MN2B_ORTHO	2	0,670691	0,329309				MN	B			
RE3B_E1A	2	3	1				RE	B			
RE7B3_D102	2	7	3				RE	B			
REB2	2	1	2				RE% B	B			
B12U	2	0,923	0,077				B	U			
B4U	2	0,8	0,2				B	U			
B2U	2	0,667	0,333				B	U			
BZR	2	1	1				B	ZR			
B122R	2	12	1				B	ZR			
B2ZR	2	2	1				B	ZR			
B4ZR3	2	4	3				B	ZR			
BACU	1	1					BA1CU				
BACU13	1	1					BA1CU13				
BAMG2_C14	2	0,333	0,667				BA	MG			
BA6MG23_D8A	2	0,207	0,793				BA	MG			
BA2MG17	2	0,105	0,895				BA	MG			
BI2CE	2	2	1				BI	CE			
BICE_B1	2	1	1				BI	CE			
BI3CE4_D73	2	3	4				BI	CE			
BI3CE5_D88	2	3	5				BI	CE			
BICE2	2	1	2				BI	CE			
BI2GD	2	2	1				BI	GD			
BIGD_B1	2	1	1				BI	GD			
BI3GD4_D73	2	3	4				BI	GD			
BI3GD5	2	3	5				BI	GD			
BIHO_B1	2	1	1				BI	HO			
BI3HO5	2	3	5				BI	HO			

Phase Name	Number of Sublattices	Stoichiometry					Occupancy				
		SL1	SL2	SL3	SL4	SL5	SL1	SL2	SL3	SL4	SL5
BIIN	2	0,5	0,5				BI	IN			
BIIN_EPSILON	1	1					BI IN				
BIIN_BRASS	2	0,333333	0,666667				BI	IN			
BI3IN5	2	0,375	0,625				BI	IN			
BIK3A	2	0,25	0,75				BI	K			
BIK3B	2	0,25	0,75				BI	K			
BI2K	2	0,666667	0,333333				BI	K			
BI2K3	2	0,4	0,6				BI	K			
BI4K5	2	0,444444	0,555556				BI	K			
BI2LU	2	2	1				BI	LU			
BILU_B1	2	1	1				BI	LU			
BI3LU5	2	3	5				BI	LU			
BI2ND	2	2	1				BI	ND			
BIND_B1	2	1	1				BI	ND			
BI3ND4_D73	2	3	4				BI	ND			
BI3ND5_D88	2	3	5				BI	ND			
BIND2	2	1	2				BI	ND			
BINI	3	1	1	1			NI,VA	VA		BI	
BI3NI	2	0,75	0,25				BI	NI			
BITB	2	1	1				BI	TB			
BI3TB4	2	3	4				BI	TB			
BI3TB5_ALPHA	2	3	5				BI	TB			
BI3TB5_BETA	2	3	5				BI	TB			
BI2PD	2	2	1				BI	PD			
BIPD	2	1	1				BI	PD			
BI3PD5	1	1					BI PD				
BIPD3	2	1	3				BI	PD			
BI3SE2	2	3	2				BI	SE		SE	
BISE	3	2	1	2			BI	BI SE			
BI2SE3_C33	2	2	3				BI	SE			
BITL_EPSILON	1	1					BI TL				
BITM	2	1	1				BI	TM			
BI3TM5	2	3	5				BI	TM			
BIY	2	1	1				BI	Y			
BI3Y5	2	3	5				BI	Y			
FCC_B1	2	1	1				U	C C2 N VA			
BCT_U	2	1	1				U	C C2 VA			
CE2C3_D5C	2	2	3				CE	C			
CEC2_C11A	2	1	2				CE	C			
CEC2_BETA	2	1	2				CE	C			
Li2C2_ALPHA	2	1	1				LI	C			
Li2C2_C1	2	1	1				LI	C			
LIC6	2	1	6				LI	C			
MG2C3	2	2	3				MG	C			
MGC2	2	1	2				MG	C			
C3U2	2	2	3				U	C			
CACU	1	1					CA1CU				
CACU5	1	1					CA1CU5				
CA2CU	1	1					CA2CU				
CAGA	2	1	1				CA	GA			
CA11GA7	2	11	7				CA	GA			
CAGA2	2	1	2				CA	GA			
CAGA4	2	1	4				CA	GA			
CA25GA59	2	25	59				CA	GA			
CA28GA11	2	28	11				CA	GA			

Phase Name	Number of Sublattices	Stoichiometry					Occupancy				
		SL1	SL2	SL3	SL4	SL5	SL1	SL2	SL3	SL4	SL5
CA3GA5	2	3	5				CA	GA			
CA3GA8	2	3	8				CA	GA			
CA5GA3	2	5	3				CA	GA			
CD6GD	2	6	1				CD	GD			
CD58GD13	2	58	13				CD	GD			
CD45GD11	2	45	11				CD	GD			
CD3GD_D019	2	3	1				CD	GD			
CD2GD	2	2	1				CD	GD			
CDGD_B2	2	1	1				CD	GD			
CAH_GAMMA	2	1	0,5				CA	H,V,A			
CAH2_ALPHA	2	1	2				CA	H			
CAH2_BETA	2	1	2				CA	H			
CALI2	2	1	2				CA	LI			
CAMG2	1	1					CA1MG2				
CA2PB_C37	2	2	1				CA	PB			
CA5PB3	2	5	3				CA	PB			
CAPB_L10	2	1	1				CA	PB			
CAPB3_L12	2	1	3				CA	PB			
CASI	2	1	1				CA	SI			
CASI2	2	1	2				CA	SI			
CA2SI	2	2	1				CA	SI			
CA3SI4	2	3	4				CA	SI			
CA5SI3	2	5	3				CA	SI			
CA14SI19	2	14	19				CA	SI			
D23_CAZN13	2	1	13				CA	ZN			
D2D_CAZN5	2	1	5				CA	ZN			
CA3ZN	2	3	1				CA	ZN			
CA5ZN3	2	5	3				CA	ZN			
CAZN	2	1	1				CA	ZN			
CAZN11	2	1	11				CA	ZN			
CAZN2	2	1	2				CA	ZN			
CAZN3	2	1	3				CA	ZN			
CD3IN	2	3	1				CD	IN			
CDIN_ALPHA	1	1					CD IN				
CD11NA2_D8C	2	11	2				CD	NA			
CD2NA	2	2	1				CD	NA			
CDSB_OMEGA	2	1	1				CD ZN	SB			
CD6Y	2	6	1				CD	Y			
CD58Y13	2	58	13				CD	Y			
CD45Y11	2	45	11				CD	Y			
CD3Y	2	3	1				CD	Y			
CD2Y	2	2	1				CD	Y			
CDY_B2	2	1	1				CD	Y			
CEFE2_C15	2	1	2				CE	FE			
CE2FE17	2	2	17				CE	FE			
CEMG	2	1	1				CE	MG			
CEMG2	2	1	2				CE	MG			
CEMG3	2	1	3				CE	MG			
CEMG12	2	1	12				CE	MG			
CE2MG17	2	2	17				CE	MG			
CE5MG41	2	5	41				CE	MG			
CE7NI3	2	7	3				CE	NI			
CENI	2	1	1				CE	NI			
CENI2	2	1	2				CE	NI			
CENI3	2	1	3				CE	NI			

Phase Name	Number of Sublattices	Stoichiometry					Occupancy				
		SL1	SL2	SL3	SL4	SL5	SL1	SL2	SL3	SL4	SL5
CE2Ni7	2	2	2	7			CE	NI			
CENi5	2	1	1	5			CE	NI			
CE2SB	2	2	2	1			CE	SB			
CE4SB3_D73	2	4	3				CE	SB			
CESB_B1	2	1	1	1			CE	SB			
CESB2	2	1	2				CE	SB			
CE5Si3_D8L	2	5	3				CE	SI			
CE3Si2_D5A	2	3	2				CE	SI			
CE5Si4	2	5	4				CE	SI			
CESi_B27	2	1	1	1			CE	SI			
CE3Si5	2	3	5				CE	SI			
CESi2_CC	2	1	2				CE	SI			
CO2CE	1	1					CO2CE				
CO3CE	1	1					CO3CE				
CO5CE	1	1					CO5CE				
CO7CE2	1	1					CO7CE2				
CO11CE24	1	1					CO11CE24				
CO17CE2	1	1					CO17CE2				
CO19CE5	1	1					CO19CE5				
CODY3	2	1	3				CO	DY			
CO7DY12	2	7	12				CO	DY			
CO2DY	2	2	1				CO	DY			
CO3DY	2	3	1				CO	DY			
CO7DY2	2	7	2				CO	DY			
CO5DY	2	5	1				CO	DY			
CO17DY2	2	17	2				CO	DY			
CO17ER2	2	17	2				CO	ER			
CO5ER_D2D	2	5	1				CO	ER			
CO7ER2	2	7	2				CO	ER			
CO3ER	2	3	1				CO	ER			
CO2ER_C15	2	2	1				CO	ER			
CO7ER12	2	7	12				CO	ER			
COER3_D011	2	1	3				CO	ER			
COGA	2	0,5	0,5				CO VA	CO GA			
COGA3	2	1	3				CO	GA			
CO17GD2	2	17	2				CO	GD			
CO5GD	2	5	1				CO	GD			
CO7GD2	2	7	2				CO	GD			
CO3GD	2	3	1				CO	GD			
CO2GD	2	2	1				CO	GD			
CO3GD4	2	3	4				CO	GD			
COGD3	2	1	3				CO	GD			
CO23GD6	2	23	6				CO	GD			
COGE	2	1	1				CO	GE			
CO3GE	2	3	1				CO	GE			
COGE2	2	1	2				CO	GE			
CO5GE2	2	5	2				CO	GE			
CO5GE3	2	5	3				CO	GE			
CO5GE7	2	5	7				CO	GE			
CO11HF2	2	11	2				CO	HF			
CO23HF6_D8A	2	23	6				CO	HF			
COHF2	2	1	2				CO% HF	CO HF%			
COIN2	2	1	2				CO	IN			
COIN3	2	1	3				CO	IN			
CO3MO	2	3	1				CO	MO			

Phase Name	Number of Sublattices	Stoichiometry					Occupancy				
		SL1	SL2	SL3	SL4	SL5	SL1	SL2	SL3	SL4	SL5
CONB_MU	4	1	2	4	6		CO NB	NB CO	NB	CO	
CONB_LAMBDA	2	2	1				CO NB	NB CO			
CO3NB	1	1					CO3NB				
CO7NB2	1	1					CO7NB2				
CO16NB9	1	1					CO16NB9				
COPT	1	1					CO PT				
COPT3	1	1					CO PT				
COSB_B81	3	0,3333	0,3333	0,3333			CO% VA	CO VA%	SB		
COSB2_C18	2	0,3333	0,6667				CO	SB			
COSB3_D02	2	0,25	0,75				CO	SB			
COSI2	2	1	2				CO	SI			
COSI	2	0,5	0,5				CO, SI	CO, SI			
CO2SI_ALPHA	2	2	1				CO, SI	CO, SI			
CO2SI_BETA	2	2	1				CO, SI	CO, SI			
CO3SI	2	3	1				CO	SI			
COSM3	1	1					CO1SM3				
CO2SM	1	1					CO2SM				
CO3SM	1	1					CO3SM				
CO4SM9	1	1					CO4SM9				
CO5SM	1	1					CO5SM				
CO7SM2	1	1					CO7SM2				
CO17SM2	1	1					CO17SM2				
CO19SM5	1	1					CO19SM5				
COSN	2	1	1				CO	SN			
COSN2	2	1	2				CO	SN			
CO3SN2_A	2	3	2				CO	SN			
CO3SN2_B	2	3	2				CO	SN			
COTA2	1	1					CO1TA2				
CO7TA2	1	1					CO7TA2				
COTI2	2	1	2				CO	TI			
COV3_A15	2	1	3				CO	V			
COZN	1	1					CO ZN				
CO4ZN	1	1					CO ZN				
CO2ZN15	2	0,117647	0,882353				CO	ZN			
COZN7	2	0,125	0,875				CO	ZN			
COZN14	2	0,071429	0,928571				CO	ZN			
CO3W	2	3	1				CO NI	W			
CO7Y2	2	7	2				CO	Y			
CO3Y	2	3	1				CO	Y			
CO2Y	2	2	1				CO	Y			
CO3Y2	2	3	2				CO	Y			
CO7Y6	2	7	6				CO	Y			
COY	2	1	1				CO	Y			
CO3Y4	2	3	4				CO	Y			
CO5Y8	2	5	8				CO	Y			
COY3	2	1	3				CO	Y			
CO17Y2	3	1	2	15			CO2 Y	CO2 Y		CO	
CO5Y	3	1	4	1			CO2 Y	CO	CO VA		
CO11ZR2	2	0,846	0,154				CO	ZR			
CO4ZR	2	0,8	0,2				CO	ZR			
CO2ZR	2	0,68	0,32				CO	ZR			
COZR	2	0,5	0,5				CO	ZR			
COZR2	2	0,333	0,667				CO	ZR			
COZR3	2	0,25	0,75				CO	ZR			
CR3GA	2	3	1				CR	GA			

Phase Name	Number of Sublattices	Stoichiometry					Occupancy				
		SL1	SL2	SL3	SL4	SL5	SL1	SL2	SL3	SL4	SL5
CRGA	2	1	1				CR	GA			
CR5GA6	2	5	6				CR	GA			
CRGA4	2	1	4				CR	GA			
CR3GE	2	0,75	0,25				CR,GE	CR,GE			
CR5GE3	2	0,625	0,375				CR,GE	CR,GE			
LCR5GE3	2	0,625	0,375				CR,GE	CR,GE			
CR11GE8	2	0,579	0,421				CR	GE			
CRGE	2	0,5	0,5				CR	GE			
CR11GE19	2	0,367	0,633				CR	GE			
CRHF_C14	2	2	1				CR HF	CR HF			
CRHF_C15	2	2	1				CR HF	CR HF			
CR3MN5	2	3	5				CR	MN TI			
CRNI2	2	1	2				CR%,MO,W	MO,NI%,W			
CRPD	2	0,5	0,5				CR	PD			
CR2PD3	2	0,4	0,6				CR	PD			
A15_CR3PT	2	0,8	0,2				CR	PT			
L12_CRPT2	1	1					CR,PT				
CR2RU	2	2	1				CR	RU			
CR3RU	2	3	1				CR	RU			
CRSI2	2	1	2				CR TI SI	CR SI			
CR3SI_A15	3	3	1	3			CR FE SI TI	CR SI AL NB	C VA		
CR5SI3	2	5	3				CR FE TI	SI			
CRZN13	2	1	13				CR	ZN			
CRZN17	2	1	17				CR	ZN			
CS2IN3	2	2	3				CS	IN			
CSIN3	2	1	3				CS	IN			
CSNA_S	2	1	2				CS	NA			
CU7AS3	2	7	3				CU	AS			
CU3AS	2	3	1,15				CU	CU,AS			
CU7AS	2	7	1				CU	AS			
CUCE	1	1					CU1CE				
CU2CE	1	1					CU2CE				
CU4CE	1	1					CU4CE				
CU5CE	1	1					CU5CE				
CU6CE	1	1					CU6CE				
CUER	2	1	1				CU	ER			
CU2ER	2	2	1				CU	ER			
CU5ER	2	5	1				CU	ER			
CU7ER2	2	7	2				CU	ER			
CU9ER2	2	9	2				CU	ER			
CU5EU	2	5	1				CU	EU			
CU2EU	2	2	1				CU	EU			
CUEU	2	1	1				CU	EU			
CUEU2	2	1	2				CU	EU			
CUGA_ZETAP	2	0,778	0,222				CU	GA			
CUGA2	2	1	2				CU	GA			
CU9GA4_GAMMA1	4	6	3	3	1		CU	CU,GA	CU,GA	GA	
CU9GA4_GAMMA2	4	3	3	3	4		CU	CU,VA	CU,GA	GA	
CU9GA4_GAMMA3	3	6	3	4			CU,VA	CU,GA			
CU3GE	1	1					CU3GE				
CUIN_BETA	2	4	1				CU	IN			
CUIN_ETA	3	0,545	0,122	0,333			CU, NI	CU, IN, SN	IN, SN		
CUIN_ETAP	2	0,64	0,36				CU	IN			
CUIN_DELTA	2	0,7	0,3				CU	IN SN			
CUIN_GAMMA	3	0,654	0,115	0,231			AG,CU	AG,CU,IN	IN,SN		

Phase Name	Number of Sublattices	Stoichiometry					Occupancy				
		SL1	SL2	SL3	SL4	SL5	SL1	SL2	SL3	SL4	SL5
CU1N_THETA	2	0,55	0,45				CU	IN			
CU2IN3SN	3	0,333	0,5	0,167			CU	IN	SN		
CU77INSN23	2	0,77	0,23				CU	IN, SN			
CU3NI27SN10	3	0,075	0,675	0,25			CU	NI	SN		
CU10HF7	2	10	7				CU	HF			
CUHF2	2	1	2				CU	HF			
CU5HF1	2	5	1				CU	HF			
CU51HF14	2	51	14				CU	HF			
CU8HF3	2	8	3				CU	HF			
CU5HO_C15B	2	5	1				CU	HO			
CU5HO_D2D	2	5	1				CU	HO			
CU9HO2	2	9	2				CU	HO			
CU7HO2	2	7	2				CU	HO			
CU2HO	2	2	1				CU	HO			
CUHO_B2	2	1	1				CU	HO			
CU37LA3	2	37	3				CU	LA			
CU6LA_ALPHA	2	6	1				CU	LA			
CU6LA_BETA	2	6	1				CU	LA			
CU5LA	2	5	1				CU	LA			
CU4LA	2	4	1				CU	LA			
CU2LA	2	2	1				CU	LA			
CULA	2	1	1				CU	LA			
CUMG2	2	1	2				CU	MG			
CUMGSI_SIGMA	3	16	6	7			CU	MG		SI	
CUMGSI_TAU	2	2	1				CU%,SI	MG			
CUND	1	1					CU1ND				
CU2ND	1	1					CU2ND				
CU4ND	1	1					CU4ND				
CU5ND	1	1					CU5ND				
CU6ND	1	1					CU6ND				
CUPD_B2	3	0,5	0,5	1			CU PD		CU PD	H VA	
CUPR	1	1					CU1PR				
CU2PR	1	1					CU2PR				
CU4PR	1	1					CU4PR				
CU5PR	1	1					CU5PR				
CU6PR	1	1					CU6PR				
CUPT_L11	2	0,5	0,5				CU% PT		CU PT%		
CUSB_ZETA	2	0,77	0,23				CU		SB		
CUSB_GAMMA	2	0,85	0,15				CU		SB		
CUSB_ETA	2	0,67	0,33				CU		SB		
CUSB_EPSILON	2	0,75	0,25				CU		SB		
CUSB_DELTA	2	0,8	0,2				CU		SB		
CU4SC_D1A	2	4	1				CU		SC		
CU2SC_C11B	2	2	1				CU		SC		
CUSC_B2	2	1	1				CU		SC		
CU15Si4_EPSILON	2	15	4				CU		SI		
CU19Si6_ETA	2	19	6				CU		SI		
CU33Si7_GAMMA	2	33	7				CU		SI		
CU9Si2_DELTA	2	9	2				CU		SI		
CUSM	1	1					CU1SM				
CU2SM	1	1					CU2SM				
CU4SM	1	1					CU4SM				
CU5SM	1	1					CU5SM				
CU6SM	1	1					CU6SM				
CU3SN	2	0,75	0,25				CU, NI		IN, SN		

Phase Name	Number of Sublattices	Stoichiometry					Occupancy				
		SL1	SL2	SL3	SL4	SL5	SL1	SL2	SL3	SL4	SL5
CU6SN5_P	2	0,545	0,455				CU	SN			
CU41SN11	2	0,788	0,212				CU	IN, SN			
CU10SN3	2	0,769	0,231				CU	SN			
CUTI	2	1	1				CU TI	CU TI			
CUTI2	2	1	2				CU	TI			
CU2TI	2	2	1				CU	TI			
CU3TI2	2	3	2				CU	TI			
CU4TI	2	4	1				CU TI	CU TI			
CU4TI3	2	4	3				CU	TI			
CU5TM_C15B	2	5	1				CU	TM			
CU9TM2	2	9	2				CU	TM			
CU7TM2	2	7	2				CU	TM			
CU2TM	2	2	1				CU	TM			
CUTM_B2	2	1	1				CU	TM			
CUY	1	1					CU1Y				
CU2YR	1	1					CU2Y				
CU7Y2	1	1					CU7Y2				
CU4Y	1	1					CU4Y				
CU2YH	1	1					CU2Y				
CU6Y	2	5	1				CU		CU2 Y		
CU5YB_D2D	2	5	1				CU		YB		
CU9YB2	2	9	2				CU		YB		
CU7YB2	2	7	2				CU		YB		
CU2YB	2	2	1				CU		YB		
CUYB_B27	2	1	1				CU		YB		
CUZN_GAMMA	4	2	2	3	6		CU%,ZN	AL,CU,SI,ZN%	CU%,ZN	AL,CU,MG,SI,ZN%	
CUZR	2	1	1				CU	ZR			
CUZR2	2	1	2				CU	ZR			
CU5ZR	2	5	1				CU	ZR			
CU8ZR3	2	8	3				CU	ZR			
CU10ZR7	2	10	7				CU	ZR			
CU51ZR14	2	51	14				CU	ZR			
D_GAMMA	1	1					AL CU SI ZN				
DYNM2_C15	2	1	2				DY	MN			
DY6MN23_D8A	2	6	23				DY	MN			
DYMN12_D2B	2	1	12				DY	MN			
DY3NI_D011	2	3	1				DY	NI			
DY3NI2	2	3	2				DY	NI			
DYN1_B27	2	1	1				DY	NI			
DYN12_C15	2	1	2				DY	NI			
DYN13	2	1	3				DY	NI			
DY2NI7	2	2	7				DY	NI			
DYN14	2	1	4				DY	NI			
DY4NI17	2	4	17				DY	NI			
DYN15_D2D	2	1	5				DY	NI			
DY2NI17	2	2	17				DY	NI			
ER3NI	2	3	1				ER	NI			
ER3NI2	2	3	2				ER	NI			
ERNI	2	1	1				ER	NI			
ERNI2	2	1	2				ER	NI			
ERNI3	2	1	3				ER	NI			
ER2NI7	2	2	7				ER	NI			
ER4NI17	2	4	17				ER	NI			
ERNI4	2	1	4				ER	NI			
ER5NI22	2	5	22				ER	NI			

Phase Name	Number of Sublattices	Stoichiometry					Occupancy				
		SL1	SL2	SL3	SL4	SL5	SL1	SL2	SL3	SL4	SL5
ERN15	2	1	5				ER	NI			
ER2NI17	2	2	17				ER	NI			
ERSSB3	2	5	3				ER	SB			
ERSB_B1	2	1	1				ER	SB			
ERSB_BETA	2	1	1				ER	SB			
ERSB2	2	1	2				ER	SB			
EUMG_B2	2	1	1				EU	MG			
EUMG2_C14	2	1	2				EU	MG			
EUMG4	2	1	4				EU	MG			
EUMG5	2	1	5				EU	MG			
EU2MG17	2	2	17				EU	MG			
EU5PD2	2	5	2				EU	PD			
EU3PD2	2	3	2				EU	PD			
EUPD	2	1	1				EU	PD			
EUPD2	2	1	2				EU	PD			
EUPD3	2	1	3				EU	PD			
EUPD5	2	1	5				EU	PD			
EUPD7	2	1	7				EU	PD			
EU2SN	2	2	1				EU	SN			
EU5SN3	2	5	3				EU	SN			
EUSN	2	1	1				EU	SN			
EU3SN5	2	3	5				EU	SN			
EUSN3	2	1	3				EU	SN			
FE2R	2	2	1				FE	DY TB			
FE3R	2	3	1				FE	DY TB			
FE17R2	2	17	2				FE	DY TB			
FE23R6	2	23	6				FE	DY TB			
FE2GD	1	1					FE2GD				
FE3GD	1	1					FE3GD				
FE17GD2	1	1					FE17GD2				
FE23GD6	1	1					FE23GD6				
FE2NB_LAVES_C14	2	2	1				FE	NB			
FE17ND2	2	0,89474	0,10526				FE	ND			
FE17ND5	2	0,77273	0,22727				FE	ND			
FEPD	2	0,5	0,5				FE PD	FE PD			
FEPD3	2	0,25	0,75				FE PD	FE PD			
FE17PR2	2	17	2				FE	PR			
FE2PR	2	2	1				FE	PR			
FESB	2	1	1				FE	FE SB			
FESB2	1	1					FE1SB2				
FE2SC	2	2	1				FE	SC			
FESC7	2	1	7				FE	SC			
MSI	2	1	1				CR FE MN NI	SI			
FESI2_H	2	3	7				FE	SI			
FESI2_L	2	1	2				FE	SI			
FE2SI	2	2	1				FE	SI			
M3SI	2	3	1				FE MN	SI			
M5SI3	2	5	3				CR FE MN	SI			
FE17SM2	2	17	2				FE	SM			
FE3SM	2	3	1				FE	SM			
FE2SM	2	2	1				FE	SM			
FESN	1	1					FE1SN				
FESN2	1	1					FE1SN2				
FE3SN2	1	1					FE3SN2				
FE5SN3	1	1					FE5SN3				

Phase Name	Number of Sublattices	Stoichiometry					Occupancy				
		SL1	SL2	SL3	SL4	SL5	SL1	SL2	SL3	SL4	SL5
FE7TA6_MU	2	7	6				FE	TA			
FE2TA_LAVES_C14	2	2	1				FE	TA			
FETI	2	1	1				FE	TI			
FEU6	2	1	6				FE U	FE U			
FE2U	2	2	1				FE U	FE U			
FE17Y2	2	17	2				FE	Y			
FE23Y6	2	23	6				FE Y	Y FE			
FE3Y	2	3	1				FE	Y			
FE2Y	2	2	1				FE Y	Y FE			
FEZN_GAMMA_D82	4	0,154	0,154	0,231	0,461		FE,ZN	FE,ZN	FE,SI,ZN	ZN	
FEZN_GAMMA_D81	3	0,137	0,118	0,745			FE	FE,SI,ZN	ZN		
FEZN_DELTA	4	0,058	0,18	0,525	0,237		FE	FE,SI,ZN	ZN	ZN	
FEZN_ZETA	3	0,072	0,856	0,072			FE,VA	ZN	SI,VA,ZN		
FEUZR_EPSILON	3	30	30	40			FE	U		ZR	
FEUZR_DELTA	2	1	2				FE U ZR	FE U ZR			
FEUZR_LAMBDA	3	6	71	23			FE	U		ZR	
FEUZR_KAPPA	3	48	20	32			FE	U		ZR	
FE6W6C	3	6	6	1			FE	W		C	
FEW3C	3	1	3	1			FE	W		C	
FEZR2	2	1	2				FE ZR	FE ZR			
FEZR3	2	1	3				FE ZR	FE ZR			
FE23ZR6	1	1					FE23ZR6				
GAN	2	1	1				GA	N			
NI5GA3	2	0,63	0,37				NI	GA			
NI3GA2	2	0,6	0,4				NI	GA			
NI3GA4	2	0,43	0,57				NI	GA			
NI2GA3	2	0,4	0,6				NI	GA			
NIGA4	2	0,2	0,8				NI	GA			
MG5GA2	2	5	2				MG	GA			
MG2GA	2	2	1				MG	GA			
MGGA	2	1	1				MG	GA			
MGGA2	2	1	2				MG	GA			
MG2GA5	2	2	5				MG	GA			
GANI_B2	2	0,5	0,5				GA NI	NI VA			
GA6PT	2	0,857	0,143				GA	PT			
GA7PT3	2	0,7	0,3				GA	PT			
GA2PT	2	0,667	0,333				GA	PT			
GA3PT2	2	0,6	0,4				GA	PT			
GAPT	2	0,5	0,5				GA	PT			
GA3PT5	2	0,375	0,625				GA	PT			
GAPT2	2	0,333	0,667				GA	PT			
GAPT3	2	0,25	0,75				GA% PT	GA PT%			
GA3SC_L12	2	3	1				GA	SC			
GA2SC	2	2	1				GA	SC			
GASC_B33	2	1	1				GA	SC			
GA4SC5	2	4	5				GA	SC			
GA3SC5	2	3	5				GA	SC			
GATI3	2	1	3				GA TI	GA TI			
GATI2	2	1	2				GA	TI			
GA3TI5	2	3	5				GA	TI			
GA4TI5	2	4	5				GA TI	GA TI			
GATI	2	1	1				GA TI	GA TI			
GA3T12	2	3	2				GA	TI			
GA2TI	2	2	1				GA	TI			
GA3TI	2	3	1				GA	TI			

Phase Name	Number of Sublattices	Stoichiometry					Occupancy				
		SL1	SL2	SL3	SL4	SL5	SL1	SL2	SL3	SL4	SL5
GDGE	2	1	1				GD	GE			
GD5GE3	2	5	3				GD	GE			
GD5GE4	2	5	4				GD	GE			
GD3GE5_A	2	3	5				GD	GE			
GD41GE59_A	2	41	59				GD	GE			
GD14GE36	2	1	2,57				GD	GE			
GD3GE5_B	2	3	5				GD	GE			
GD41GE59_B	2	41	59				GD	GE			
GD2GE3	2	2	3				GD	GE			
GDMG	1	1					GD1MG				
GDMG2	1	1					GD1MG2				
GDMG3	1	1					GD1MG3				
GDMG5	1	1					GD1MG5				
M12R	2	12	1				MN	GD			
M23R6	2	23	6				MN	GD			
M2R	2	2	1				MN	GD			
GD3NI	2	3	1				GD	NI			
GD3NI2	2	3	2				GD	NI			
GDN1	2	1	1				GD	NI			
GDN12	2	1	2				GD	NI			
GDN13	2	1	3				GD	NI			
GD2NI7	2	2	7				GD	NI			
GDN14	2	1	4				GD	NI			
GDN15	2	1	5				GD	NI			
GD2NI17	2	2	17				GD	NI			
GDSI	2	1	1				GD	SI			
GDSI2	2	1	2				GD	SI			
GD3SI5	2	3	5				GD	SI			
GD5SI3	2	5	3				GD	SI			
GD5SI4	2	5	4				GD	SI			
GEMG2	2	1	2				GE	MG			
B20_GERU	2	1	1				GE SI	RU			
ALPHA_GE3RU2	2	3	2				GE	RU			
BETA_GE3RU2	2	3	2				GE SI SN	RU			
GE4NA	2	4	1				GE	NA			
GENA	2	1	1				GE	NA			
GENA3	2	1	3				GE	NA			
GENI_B31	2	0,5	0,5				GE	NI			
GE3NI5_B82	3	1	1	1			GE	NI		NIVA	
GE3NI5_PRIME	2	0,375	0,625				GE	NI			
GENI2_C37	2	0,335	0,665				GE	NI			
GE2NI5	2	0,28	0,72				GE	NI			
GENI3_B32	2	0,256	0,744				GE	NI			
GE2PT_C18	2	2	1				GE	PT			
GE3PT2	2	3	2				GE	PT			
GEPT_B31	2	1	1				GE	PT			
GE2PT3	2	2	3				GE	PT			
GEPT2_C22	2	1	2				GE	PT			
GEPT3	2	1	3				GE% PT	PT			
GE2SR	2	2	1				GE	SR			
GESR_BF	2	1	1				GE	SR			
GE3SR5_D8L	2	3	5				GE	SR			
GESR2_C23	2	1	2				GE	SR			
GETE_LOW	2	1	1				GE% VA	TE			
GETE_B1	2	1	1				GE% VA	TE			

Phase Name	Number of Sublattices	Stoichiometry					Occupancy				
		SL1	SL2	SL3	SL4	SL5	SL1	SL2	SL3	SL4	SL5
GETE_GAMMA	2	49	51				GE	TE			
GE2TI_C54	2	2	1				GE	TI			
GE5T6	2	5	6				GE	TI			
GE3TI5_D88	2	3	5				GE	TI			
GEV3	2	1	3				GE	V			
GE31V17	2	31	17				GE	V			
GE3V5	2	3	5				GE	V			
GE8V11	2	8	11				GE	V			
NDNI5H3	4	1	5	3	6		ND	NI	H	H VA	
NDNI5H6	4	1	5	3	6		ND	NI	H	H VA	
HFNIA	2	1	1				HF	NI			
HFNI3A	2	1	3				HF	NI			
HFNI3B	2	1	3				HF	NI			
HFNI5	2	1	5				HF	NI			
HF2NI7	2	2	7				HF	NI			
HF3NI7	2	3	7				HF	NI			
HF7NI10	2	7	10				HF	NI			
HF9NI11	2	9	11				HF	NI			
HF8NI21	2	8	21				HF	NI			
NIHF2	2	2	1				HF	NI VA			
HF2SI	2	2	1				HF	SI			
HF5SI3	2	5	3				HF	SI			
HF3SI2	2	3	2				HF	SI			
HF5SI4	2	5	4				HF	SI			
HFSI	2	1	1				HF	SI			
HFSI2	2	1	2				HF	SI			
HF5SN3_D88	2	5	3				HF	SN			
HF5SN4	2	5	4				HF	SN			
HFSN2_C40	2	1	2				HF	SN			
HGPB2_L10	2	1	2				HG	PB			
NDH_GAMMA	2	1	2				ND	H VA			
NDH2	3	1	2	1			ND	H VA		H VA	
HG2MG_C11B	2	2	1				HG	MG			
HGMG_B2	2	1	1				HG	MG			
HG3MG5_D88	2	3	5				HG	MG			
HGMG2_C37	2	1	2				HG	MG			
HG2MG5	2	2	5				HG	MG			
HGMG3	2	1	3				HG	MG			
HGSN38_B	2	1	38				HG	SN			
HGSN12_G	2	1	6				HG VA	SN			
HGSN4	2	1	4				HG	SN			
HGSN7_D	2	1	7				HG	SN			
HG3ZN	2	0,75	0,25				HG	ZN			
HGZN2	2	1	2				HG	ZN			
HGZN3	2	1	3				HG	ZN			
HOMN2	2	2	1				MN	HO			
MN23M6_D8A	2	0,793	0,207				MN	HO SM			
HOMN12_D2B	2	12	1				MN	HO			
ALPHA_INEU2	2	1	2				IN	EU			
BETA_INEU2	2	1	2				IN	EU			
INEU	2	1	1				IN	EU			
IN2EU	2	2	1				IN	EU			
IN4EU	2	4	1				IN	EU			
IN3LA	2	3	1				IN	LA			

Phase Name	Number of Sublattices	Stoichiometry					Occupancy				
		SL1	SL2	SL3	SL4	SL5	SL1	SL2	SL3	SL4	SL5
IN2LA	2	2	1				IN	LA			
IN5LA3	2	5	3				IN	LA			
IN5TLA43	2	57	43				IN	LA			
INLA	2	1	1				IN	LA			
INLA2	2	1	2				IN	LA			
INLA3	2	1	3				IN	LA			
NI2IN3	2	2	3				NI	IN			
NIIN	2	1	1				NI	IN			
NI3IN7	2	3	7				NI	IN			
NI3IN	2	3	1				NI	IN			
NI2IN	2	2	1				NI	IN			
INNI_ZETA	3	1	1	1			NI,VA	NI	IN,NI		
INNI_ZETA_PRIME	3	1	1	1			NI,VA	NI	IN		
INNI_DELTA	2	1	1				NI,VA	IN,NI			
INPD2_BETA	2	0,34	0,66				IN	PD			
INPD3_BETA	2	0,26	0,74				IN	PD			
INPD2_ALPHA	2	0,333	0,667				IN	PD			
INPD3_ALPHA	2	0,25	0,75				IN	PD			
IN7PD3	2	0,71	0,29				IN	PD			
IN3PD2	2	0,6	0,4				IN	AG,PD			
IN3PD5	2	0,375	0,625				IN	PD			
IN7PT3_D8F	2	7	3				IN	PT			
IN2PT_C1	2	2	1				IN	PT			
IN3PT2_D513	2	3	2				IN	PT			
INPT_HT	2	1	1				IN% PT	IN PT%			
IN5PT6	2	5	6				IN% PT	IN PT%			
IN9PT13	2	9	13				IN	IN PT%			
IN2PT3_ALPHA	2	2	3				IN	PT			
IN2PT3_B82	2	2	3				IN% PT	IN PT%			
INPT2	2	1	2				IN	PT			
IN4SE3	2	4	3				IN	SE			
INSE	2	1	1				IN	SE			
IN6SE7	2	6	7				IN	SE			
IN9SE11	2	9	11				IN	SE			
IN5SE7	2	5	7				IN	SE			
IN2SE3_C33	2	2	3				IN	SE			
IN2SE3_BETA	2	2,02	2,98				IN	SE			
IN2SE3_GAMMA	2	2	3				IN	SE			
IN2SE3_DELTA	2	2	3				IN	SE			
INSN_GAMMA	1	1					IN SN				
IN3YB	2	3	1				IN	YB			
IN2YB	2	2	1				IN	YB			
INYB2	2	1	2				IN	YB			
IN2YB5	2	2	5				IN	YB			
IR3ZR5	2	3	5				IR	ZR			
IR2ZR	2	2	1				IR	ZR			
IRZR2	2	1	2				IR	ZR			
IRZR3	2	1	3				IR	ZR			
IR3ZR	2	3	1				IR ZR	IR ZR			
IRZR_ALPHA	2	1	1				IR ZR	ZR			
IRZR_BETA	2	1	1				IR ZR	IR ZR			
KNA2_C14	2	1	2				K	NA			
LAH3	3	1	2	1			LA	H VA	H VA		
LAMG3	2	1	3				LA%,MG	MG			
LAMG12	2	1	12				LA%,MG	LA, MG%			

Phase Name	Number of Sublattices	Stoichiometry					Occupancy				
		SL1	SL2	SL3	SL4	SL5	SL1	SL2	SL3	SL4	SL5
LAGM	2	1	1				LA	MG			
LAMG2	2	1	2				LA	MG			
LA2MG17	2	2	17				LA	MG			
LANI	1	1					LA1NI				
LANI3	1	1					LA1NI3				
LANI5	1	1					LA1NI5				
LA2NI3	1	1					LA2NI3				
LA2NI7_ALPHA	1	1					LA2NI7				
LA2NI7_BETA	1	1					LA2NI7				
LA3NI	1	1					LA3NI				
LA7NI3	1	1					LA7NI3				
LA7NI16	1	1					LA7NI16				
LA2SB	2	2	1				LA	SB			
LA3SB2	2	3	2				LA	SB			
LASB_B1	2	1	1				LA	SB			
LASB2	2	1	2				LA	SB			
LA5SN3_D8M	2	0.625	0.375				LA	SN			
LA5SN3_D88	2	0.625	0.375				LA	SN			
LA5SN4	2	0.555	0.445				LA	SN			
LA11SN10	2	0.524	0.476				LA	SN			
LASN_B33	2	0.5	0.5				LA	SN			
LA2SN3	2	0.4	0.6				LA	SN			
LA3SN5	2	0.375	0.625				LA	SN			
LASN3_L12	2	0.25	0.75				LA	SN			
LIH	2	1	1				LI	H			
LI3N	2	3	1				LI	N			
LI4PB	2	4	1				LI	PB			
LI7PB2	2	7	2				LI	LI PB%			
LI3PB_D03	2	3	1				LI	PB			
LI5PB2	2	5	2				LI	PB			
LIPB_ALPHA	2	1	1				LI% PB	LI PB%			
LIPB_B2	2	1	1				LI% PB	LI PB%			
LI7SI3	1	1					LI7SI3				
LI12SI7	1	1					LI12SI7				
LI13SI4	1	1					LI13SI4				
LI22SI5	1	1					LI22SI5				
LI22SN5	2	22	5				LI	SN			
LI7SN2	2	7	2				LI	SN			
LI13SN5	2	13	5				LI	SN			
LI5SN2	2	5	2				LI	SN			
LI7SN3	2	7	3				LI	SN			
LISN	2	1	1				LI	SN			
LI2SN5	2	2	5				LI	SN			
LI23SR6_D8A	2	23	6				LI	SR			
LI2SR3	2	2	3				LI	SR			
LU3SB	2	3	1				LU	SB			
LU5SB3	2	5	3				LU	SB			
LUSB_B1	2	1	1				LU	SB			
LUSB_BETA	2	1	1				LU	SB			
LUSB2	2	1	2				LU	SB			
MG2NI	2	2	1				MG	NI			
M6SI5	2	6	5				CR,TI	SI			
MG3LN	2	3	1				MG	DY			
MG12PR	2	12	1				MG	PR			
MG41PR5	2	41	5				MG,PR	MG,PR			

Phase Name	Number of Sublattices	Stoichiometry					Occupancy				
		SL1	SL2	SL3	SL4	SL5	SL1	SL2	SL3	SL4	SL5
MGPR_B2	2	1	1				MG,PR	MG,PR			
MG2PR	2	2	2	1			MG	PR			
MG3PR	2	3	1				MG	MG,PR			
MG2RE	2	2	1				MG	ND			
MG41RE5	2	41	5				MG	ND			
MG3RE	2	3	1				MG	MG ND			
MG5RE	2	5	1				MG	ND			
MGSC	1	1					MG1SC				
MG2SI	2	2	1				MG	SI			
MG41SM5	2	41	5				MG	SM			
MG5SM	2	5	1				MG	SM			
MG3SM_D03	2	3	1				MG	SM			
MG2SM_C15	2	2	1				MG	SM			
MG2SN	1	1					MG2SN				
MG17SR2	2	17	2				MG	SR			
MG38SR9	2	38	9				MG	SR			
MG23SR6	2	23	6				MG	SR			
MG2TB	2	2	1				MG	MG TB			
MG3TB	2	3	1				MG	MG TB			
MG24TB5	2	24	5				MG	TB			
MG5TB	2	5	1				MG	TB			
MG24TM5	2	24	5				MG	TM			
MG2TM	2	2	1				MG	TM			
MGTM_B2	2	1	1				MG VA	MG TM			
MG2Y	2	2	1				MG Y	MG ND Y			
MG24Y5	3	24	4	1			MG	MG Y			Y
MGYB_LAVES_C14	2	2	1				MG YB	MG YB			
MGZN	2	12	13				MG	AL CU ZN			
MG2ZN3	2	2	3				MG	AL CU ZN			
MG2ZN11	3	2	6	5			MG	CU ZN			
MG7ZN3	2	51	20				MG	ZN			
MNMO_LAVES_PHASE	2	2	1				MN	MO			
MN23PR6_D8A	2	23	6				MN	PR			
MN23SC6	2	23	6				MN	SC			
MN2SC	2	2	1				MN	SC			
MNSC4	2	1	4				MN	SC			
MN6SI	2	0,857143	0,142857				MN	SI			
MN9SI2	2	0,818182	0,181818				MN	SI			
MN5SI2	2	0,714286	0,285714				MN	SI			
MN11SI19	2	0,366667	0,633333				MN	SI			
MN2SM_LAVES_C14	2	2	1				MN	SM			
MN19SN6	2	19	6				MN	SN			
MN2SN	2	2	1				MN	SN			
MNSN2	2	1	2				MN	SN			
MN3TI	2	3	1				CR MN	TI			
MN4TI	2	0,815	0,185				CR MN	TI			
TIMN_ALPHA	2	1	1				CR MN	TI			
TIMN_BETA	2	0,515	0,485				CR MN	TI			
MN12Y	2	12	1				MN	Y			
MN23Y6	2	23	6				MN	Y			
MN2Y	2	2	1				MN	Y			
MNZN9	2	1	9				MN	ZN			
MN2ZR	2	2	1				MN ZR	MN ZR			
MONI4_BETA	2	1	4				MO	NI			
MONI3 GAMMA	2	1	3				MO	NI			

Phase Name	Number of Sublattices	Stoichiometry					Occupancy				
		SL1	SL2	SL3	SL4	SL5	SL1	SL2	SL3	SL4	SL5
MONI_DELTA	3	24	20	12			CR NI FE	CR MO NI FE	MO		
MO3SI	2	0,75	0,25				MO	SI			
MO5SI3	2	0,625	0,375				MO	SI			
MOSI2	2	0,333333	0,666667				MO	SI			
NAZN13	2	1	13				NA	ZN			
NBNI_MU	2	7	6				NI NB	NB			
NI3NB	2	3	1				NI NB	NB NI			
NB3SI	2	0,75	0,25				NB	SI			
NB5SI3	2	0,625	0,375				NB	SI			
NBSI2	2	1	2				NB	SI			
NBSN2	1	1					NB1SN2				
NB3SN_C15	2	3	1				NB SN	NB SN			
NB6SN5	3	24	16	4			NB	SN			NB SN
ND3NI_D011	2	3	1				ND	NI			
ND7NI3_D102	2	7	3				ND	NI			
NDNI_B33	2	1	1				ND	NI			
NDNI2_C15	2	1	2				ND	NI			
NDNI3	2	1	3				ND	NI			
ND2NI7	2	2	7				ND	NI			
NDNI5_D2D	3	1	5	3			ND	NI			H VA
ND2NI17	2	2	17				ND	NI			
NDSB	1	1					ND1SB				
NDSB2	1	1					ND1SB2				
ND2SB	1	1					ND2SB				
ND4SB3	1	1					ND4SB3				
ND5SB3	1	1					ND5SB3				
NDZN_B2	2	1	1				ND	ZN			
NDZN2	2	1	2				ND	ZN			
NDZN3	2	1	3				ND	ZN			
ND3ZN11	2	3	11				ND	ZN			
ND13ZN58	2	13	58				ND	ZN			
ND3ZN22	2	3	22				ND	ZN			
ND2ZN17	2	2	17				ND	ZN			
NDZN11	2	1	11				ND	ZN			
NISI2_C1	2	1	2				NI	SI			
NI3SI_MONOCL	2	3	1				NI	SI			
NI3SI_ORTHO	2	3	1				NI	SI			
NI2SI_C37	2	2	1				CR NI%	SI			
NI3SI2	2	3	2				NI	SI			
NI5SI2	2	5	2				CR NI%	SI			
NI5I_B31	2	1	1				NI	SI			
NI2SI_HEX	3	1	1	1			NI	NI VA			SI
NISM3	2	1	3				NI	SM			
NISM	2	1	1				NI	SM			
NI2SM	2	2	1				NI	SM			
NI3SM	2	3	1				NI	SM			
NI7SM2	2	7	2				NI	SM			
NI19SM5	2	19	5				NI	SM			
NI5SM	2	5	1				NI	SM			
NI17SM2	2	17	2				NI	SM			
NI3SB_D0A	2	3	1				NI	NI SB%			
NI3SB_D03	3	2	1	1			NI% VA	NI VA%			SB
NI5SB2_LT	2	5	2				NI	NI SB%			
NISB_B81	3	1	1	1			NI% VA	NI VA%			SB
NISB2_C18	2	1	2				NI	SB			

Phase Name	Number of Sublattices	Stoichiometry					Occupancy				
		SL1	SL2	SL3	SL4	SL5	SL1	SL2	SL3	SL4	SL5
NI5SC_D2D	2	5	1				NI	SC			
NI7SC2	2	7	2				NI	SC			
NISC2	2	7	18				NI	SC			
NI3SN2	3	0,5	0,25	0,25			NI,SN	AU,CU,NI	AU,CU,NI		
NI3SN4	3	0,25	0,25	0,5			CU,NI	NI,SN	SN		
NI3SN_LT	2	0,75	0,25				CU,NI	IN,SN			
NISR	2	1	1				NI	SR			
NI2TA	2	0,666667	0,333333				NI	TA			
NI3MOTA	2	0,75	0,25				NI TA	NI TA			
NI8TA	2	0,888889	0,111111				NI	TA			
NITA	4	0,076923	0,307692	0,153846	0,461538		NI TA	TA	NI TA	NI	
NITA2	2	0,333333	0,666667				NI TA	TA			
NI17TH2	2	19	2				NI	TH			
NI5TH_D2D	2	5	1				NI	TH			
NI7TH2_ALPHA	2	7	2				NI	TH			
NI7TH2_BETA	2	7	2				NI	TH			
NI2TH_C32	2	2	1				NI	TH			
NI7TH4	2	7	4				NI	TH			
NITH	2	1	1				NI	TH			
NI3TH7_D102	2	3	7				NI	TH			
NITI2	3	1	2	0,5			NI	TI	C VA%		
NI3TI	2	0,75	0,25				NI% TI	NI SI TI%			
TI3SIC2	3	3	1	2			TI	SI	C		
NI2V	2	2	1				NI	V			
NI3V	2	3	1				NI	V			
NI2V7	2	2	7				NI	V			
NIW	2	1	1				NI	W			
NIW2	2	1	2				NI	W			
NI4W	2	4	1				NI	W			
NI17Y2	2	17	2				NI	Y			
NI5Y	2	5	1				NI	Y			
NI4Y	2	4	1				NI	Y			
NI7Y2	2	7	2				NI	Y			
NI3Y	2	3	1				NI	Y			
NI2Y	2	2	1				NI	Y			
NIY	2	1	1				NI	Y			
NI2Y3	2	2	3				NI	Y			
NIY3	2	1	3				NI	Y			
NIZN_BETA1	1	1					NI ZN				
NIZN_DELTA	2	0,111	0,889				NI	ZN			
NIZN_GAMMA	1	1					NI ZN				
NI10ZR7	2	0,575	0,425				NI% ZR	VA ZR%			
NI11ZR9	2	0,55	0,45				NI	ZR			
NI21ZR8	2	0,725	0,275				NI	ZR			
NI3ZR	2	0,75	0,25				NI% ZR	VA ZR%			
NI5ZR	2	0,833	0,167				NI% ZR	VA ZR%			
NI7ZR2	2	0,78	0,22				CR NI	ZR			
NIZR	2	0,5	0,5				NI	ZR			
NIZR2	2	0,333	0,667				CR NI	ZR			
OSSI	2	0,5	0,5				OS	SI			
OS2Si3	2	0,4	0,6				OS	SI			
OSSI2	2	0,333333	0,666667				OS	SI			
Si2SR_ALPHA	2	2	1				SI	SR			
Si2SR_BETA	2	2	1				SI% VA	SR			
SISR_B33	2	1	1				SI	SR			

Phase Name	Number of Sublattices	Stoichiometry					Occupancy				
		SL1	SL2	SL3	SL4	SL5	SL1	SL2	SL3	SL4	SL5
SI3SR5_D8L	2	3	5				SI	SR			
SISR2_C37	2	1	2				SI	SR			
SRPB3	2	1	3				SR	PB			
SR3PB5	2	3	5				SR	PB			
SR2PB3	2	2	3				SR	PB			
SRPB	2	1	1				SR	PB			
SR5PB4	2	5	4				SR	PB			
SR5PB3	2	5	3				SR	PB			
SR2PB	2	2	1				SR	PB			
SN4P3	2	4	3				SN	P			
PT3PB	2	3	1				PT	PB			
PTPB	2	1	1				PT	PB			
PTPB4	2	1	4				PT	PB			
PBTE	2	1	1				PB	TE			
PDPB	1	1					PD1PB				
PDPB2	1	1					PD1PB2				
PD3PB	2	0.75	0.25				PD	PB PD			
PD5PB3_ALPHA	1	1					PD5PB3				
PD5PB3_BETA	3	1	1	1			PD	PB	VA PD		
PD5PB3_GAMMA	3	1	1	1			PD	PB	VA PD		
PD13PB9	1	1					PD0.59PB0.41				
PD3SC	2	3	1				PD	SC			
PD2SC	2	2	1				PD	SC			
PDSC2	2	1	2				PD	SC			
PDSC4	2	1	4				PD	SC			
PDSC	2	1	1				PD VA	SC			
PDSI	2	1	1				PD	SI			
PD19Si10	2	19	10				PD	SI			
PD39Si20	2	39	20				PD	SI			
PD2SI_BETA	2	2	1				PD,SI	SI			
PD2SI_ALPHA	2	2	1				PD,SI	SI			
PD3SI	2	3	1				PD	SI			
PD15Si4	2	15	4				PD	SI			
PD9Si2	2	9	2				PD	SI			
PD14Si3	2	14	3				PD	SI			
PD5SI	2	5	1				PD	SI			
PD21Si4	2	21	4				PD,SI	SI			
MPD3	2	1	3				PD,SM%	PD			
MSM_A	2	1	1				PD,SM	SM			
MSM_B	2	1	1				PD,SM	SM			
PD7SM	2	7	1				PD	SM			
PD5SM	2	5	1				PD	SM			
PD21SM10	2	21	10				PD	SM			
PD4SM3	2	4	3				PD	SM			
PD2SM3	2	2	3				PD	SM			
PD3SM7	2	3	7				PD	SM			
PD2SN_GAMMA	3	1	1	1			PD	SN	PD,VA		
PDSN	2	0.5	0.5				PD,VA	PD,SN			
PDSN2	2	0.333	0.667				PD,SN	SN			
PDSN3	2	0.25	0.75				PB,PD	PD,SN			
PDSN4	2	0.2	0.8				PD	PB,PD,SN			
PD3SN	2	0.75	0.25				PD,SN	SN,PD			
PD3SN2_ALPHA	2	0.6	0.4				PD	SN			
PD3SN2_BETA	2	0.6	0.4				PD	SN			
PD3SN2_DELTA	2	0.59	0.41				PD	SN			

Phase Name	Number of Sublattices	Stoichiometry					Occupancy				
		SL1	SL2	SL3	SL4	SL5	SL1	SL2	SL3	SL4	SL5
PD2SN	2	0,667	0,333				PD	SN			
PD20SN13	2	0,6	0,4				PD,SN	PD,SN			
PD3TB	2	3	1				PD	PD,TB%			
PD7TB	2	7	1				PD	TB			
PDTB_A	2	1	1				PD%,TB	TB			
PDTB_B	2	1	1				PD%,TB	TB			
PD21TB10	2	21	10				PD	TB			
PD3TB2_A	2	3	2				PD	TB			
PD3TB2_B	2	3	2				PD	TB			
PD4TB3	2	4	3				PD	TB			
PD2TB3	2	2	3				PD	TB			
PD2TB5	2	2	5				PD	TB			
PDZN_GAMMA	2	2	9				PD,ZN	PD,ZN			
PDZN_BETA	2	1	1				PD%,ZN	PD,ZN%			
PDZN_1BETA	2	1	1				PD%,ZN	PD,ZN%			
PDZN2	2	1	2				PD	ZN			
PD2ZN	2	2	1				PD	ZN			
PDZN_ETA	2	0,09	0,91				PD	ZN			
PD3ZR	2	3	1				PD ZR	PD ZR			
PDZRM	3	1	1	1			PD	ZR			
PD4ZR3	2	4	3				PD	ZR			
PD11ZR9	2	11	9				PD	ZR			
PDZR_ALPHA	2	1	1				PD	ZR			
PDZR_BETA	2	1	1				PD	ZR			
PDZR_GAMMA	2	1	1				PD VA	PD ZR			
PRSB	1	1					PR1SB				
PRSB2	1	1					PR1SB2				
PR2SB	1	1					PR2SB				
PR4SB3	1	1					PR4SB3				
PR5SB3	1	1					PR5SB3				
PT7SB	2	7	1				PT	SB			
PT5SB_L12	2	5	1				PT% SB	PT SB%			
PT3SB_D023	2	3	1				PT	SB			
PT3SB2	2	3	2				PT	SB			
PTSB_B81	2	1	1				PT	SB			
PTSB2_C2	2	1	2				PT	SB			
PTSI	2	1	1				PT	SI			
PT782SI218	2	0,782	0,218				PT	SI			
PT5SI2	2	0,714	0,286				PT	SI			
PT6SI5	2	6	5				PT	SI			
PT17SI8_ALPHA	2	17	8				PT	SI			
PT2SI_ALPHA	2	2	1				PT	SI			
PT3SI_ALPHA	2	3	1				PT	SI			
PT17SI8_BETA	2	17	8				PT	SI			
PT2SI_BETA	2	2	1				PT	SI			
PT3SI_BETA	2	3	1				PT	SI			
PT3SN_L12	2	3	1				PT	SN			
PTSN_B81	2	1	1				PT	SN			
PT2SN3	2	2	3				PT	SN			
PTSN2_C1	2	1	2				PT	SN			
PTSN4_D1C	2	1	4				PT	SN			
PTTA_SIGMA	1	1					PT TA				
PT2TA	2	0,667	0,333				PT	TA			
PT3TA	2	0,75	0,25				PT	TA			
PTTA	2	0,5	0,5				PT	TA			

Phase Name	Number of Sublattices	Stoichiometry					Occupancy				
		SL1	SL2	SL3	SL4	SL5	SL1	SL2	SL3	SL4	SL5
PTTA6	2	0,143	0,857				PT	TA			
PT8TI	2	8	1				PT	TI			
PT3TI	2	1	3				PT, TI	PT			
PTTI_ALPHA	2	1	1				PT, TI	PT, TI			
PTTI_BETA	2	1	1				PT, TI	PT, TI			
PT3TI4	2	3	4				PT	TI			
PTTI3	2	3	1				PT, TI	PT, TI			
PT3V_D022	2	3	1				PT% V	PT V%			
PT2V	2	2	1				PT% V	PT V%			
PTV_B19	2	1	1				PT% V	PT V%			
PTV3_A15	2	1	3				PT% V	PT V%			
PUC_B1	2	1	1				PU	C% VA			
PU3C2	2	0,6	0,4				PU	C			
PU2C3_D5C	2	0,4	0,6				PU	C			
PUC2_C11A	2	1	2				PU	C			
RE2SI	2	2	1				RE	SI			
RESI_B20	2	1	1				RE	SI			
RESI2	2	1	2				RE	SI VA			
RE24TI5_A12	2	24	5				RE	TI			
RETI_B2	2	1	1				RE	TI			
RU2SI	2	2	1				RU	SI			
RU4SI3	2	4	3				RU	SI			
RU3SN7	2	3	7				RU	GE SN			
RU2SN3	2	2	3				RU	GE SN			
RUZR	2	1	1				RU	ZR			
RU2ZR	2	2	1				RU	ZR			
SBSN	2	1	1				BI, IN, PB, SB, SN	BI, IN, SB, SN			
SB2SN3	2	2	3				SB	SN			
SB2TB	2	2	1				SB	TB			
SBTB_B1	2	1	1				SB	TB			
SBTB_BETA	2	1	1				SB	TB			
SB3TB4_D73	2	3	4				SB	TB			
SB3TB4_BETA	2	3	4				SB	TB			
SB3TB5_D88	2	3	5				SB	TB			
SB2TM	2	2	1				SB	TM			
SBTM_B1	2	1	1				SB	TM			
SBTM_BETA	2	1	1				SB	TM			
SB3TM5_ALPHA	2	3	5				SB	TM			
SB3TM5_BETA	2	3	5				SB	TM			
SBY_B1	2	1	1				SB	Y			
SB3Y4_D73	2	3	4				SB	Y			
SB3Y5_D88	2	3	5				SB	Y			
SBY3	2	1	3				SB	Y			
SBZN_BETA	2	0,5	0,5				SB	ZN			
SBZN_DELTA	2	0,425	0,575				SB	ZN			
SBZN_ZETA	2	0,4	0,6				SB	ZN			
SBZN_EPSILON	2	0,425	0,575				SB	ZN			
SBZN_ETA	2	0,38	0,62				SB	ZN			
SBZN_GAMMA	2	0,45	0,55				SB	ZN			
SCSI	2	1	1				SC	SI			
SC2SI3	2	2	3				SC	SI			
SC5SI3	2	5	3				SC	SI			
SI3N4	2	3	4				SI	N			
TA2SI	2	0,666667	0,333333				TA	SI			
TA3SI	2	0,75	0,25				TA	SI			

Phase Name	Number of Sublattices	Stoichiometry					Occupancy				
		SL1	SL2	SL3	SL4	SL5	SL1	SL2	SL3	SL4	SL5
TASi2	2	0,333333	0,666667				TA	SI			
TA5Si3	2	0,625	0,375				TA	SI			
TISI	2	1	1				TI	SI			
TI3Si	2	3	1				TI	SI			
TISi2	2	1	2				CR TI	SI			
D88_M5Si3	4	2	3	3	1		CR% SI TI%	CR SI% TI	CR NI TI	C N VA%	
Ti5Si4	2	5	4				TI	SI			
B27_SIU	2	0,511	0,489				SI	U			
C32_Si5U3	2	0,625	0,375				SI	U			
L12_Si3U	2	0,75	0,25				SI	U			
L12_SiU3_H	2	0,25	0,75				SI	U			
SiU3_L	2	0,25	0,75				SI	U			
CC_Si2U	2	0,652778	0,347222				SI	U			
Si2U3	2	0,4	0,6				SI	U			
SM5SN3	2	0,625	0,375				SM	SN			
SM4SN3	2	0,571	0,429				SM	SN			
SM5SN4	2	0,556	0,444				SM	SN			
SM11SN10	2	0,524	0,476				SM	SN			
SM2SN3	2	0,4	0,6				SM	SN			
SMSN2	2	0,333	0,667				SM	SN			
SMSN3	2	0,25	0,75				SM	SN			
SMZN_B2	2	1	1				SM	ZN			
SMZN2	2	1	2				SM	ZN			
SMZN3	2	1	3				SM	ZN			
SM3ZN11	2	3	11				SM	ZN			
SM13ZN58	2	13	58				SM	ZN			
SM3ZN22	2	3	22				SM	ZN			
SM2ZN17	2	2	17				SM	ZN			
SMZN11_D2B	2	1	11				SM	ZN			
V3Si	2	3	1				SI V%	SI% V			
V5Si3	2	5	3				V	SI			
V6Si5	2	6	5				V	SI			
VSi2	2	1	2				V	SI			
V2ALC	3	2	1	1			V	AL	C		
V3ALC2	3	3	1	2			V	AL	C		
V4ALC3	4	4	1	2	1		V	AL	C	C VA	
WSi2	2	0,666667	0,333333				SI	W			
W5Si3	2	0,375	0,625				SI	W			
YSi	2	1	1				SI	Y			
YSi2_H	2	2	1				SI	Y			
YSi2_R	2	2	1				SI	Y			
Y5Si3	2	3	5				SI	Y			
Y5Si4	2	4	5				SI	Y			
Y3Si5_R	2	5	3				SI	Y			
Y3Si5_H	2	5	3				SI	Y			
YBSi174	2	1,74	1				SI	YB			
YB3Si5	2	5	3				SI	YB			
YB8Si11	2	11	8				SI	YB			
YBSi	2	1	1				SI	YB			
YB5Si4	2	4	5				SI	YB			
YB5Si3	2	3	5				SI	YB			
ZRSi	2	1	1				SI	ZR			
ZR2Si	2	1	2				SI	ZR			
ZR3Si	2	1	3				SI	ZR			
ZRSi2	2	2	1				SI	ZR			

Phase Name	Number of Sublattices	Stoichiometry					Occupancy				
		SL1	SL2	SL3	SL4	SL5	SL1	SL2	SL3	SL4	SL5
ZR3Si2	2	2	2	3			SI	ZR			
ZR5Si3	2	2	3	5			SI	ZR			
ZR5Si4	2	2	4	5			SI	ZR			
SMSB	1	1					SM1SB				
SMSB2	1	1					SM1SB2				
SM2SB	1	1					SM2SB				
SM4SB3	1	1					SM4SB3				
SM5SB3	1	1					SM5SB3				
SNTI2	2	1	2				SN	TI			
SNTI3	2	1	3				SN TI		SN TI		
SN3Ti5	2	3	5				SN		TI		
SN5Ti6	2	5	6				SN		TI		
SN3V2	2	3	2				SN		V		
SNV3	2	0,205	0,795				SN		V		
SN3Y	2	3	1				SN		Y		
SN5Y2	2	5	2				SN		Y		
SN2Y	2	2	1				SN		Y		
SN10Y11	2	10	11				SN		Y		
SN4Y5	2	4	5				SN		Y		
SN3Y5	2	3	5				SN		Y		
SNZR4	2	1	4				SN		ZR		
SN2ZR	2	2	1				SN		ZR		
SN3ZR5	2	3	5				SN		ZR		
SRCU	1	1					SR1CU				
SRCU5	1	1					SR1CU5				
SRZN	2	1	1				SR		ZN		
SRZN13	2	1	13				SR		ZN		
SRZN2	2	1	2				SR		ZN		
SRZN5_ALPHA	2	1	5				SR		ZN		
SRZN5_BETA	2	1	5				SR		ZN		
TA4C3	2	0,62	0,38				TA		C		
TH2ZN_C16	2	2	1				TH		ZN		
THZN2	2	1	2				TH		ZN		
THZN4_D13	2	1	4				TH		ZN		
TH2ZN17	2	2	17				TH		ZN		
TIZN	2	2	1				TI		ZN		
TIZN	2	1	1				TI		ZN		
TIZN2	2	1	2				TI		ZN		
TIZN3	2	1	3				TI		ZN		
TIZN5	2	1	5				TI		ZN		
TIZN10	2	1	10				TI		ZN		
TIZN15	2	1	15				TI		ZN		
U2N3_ALPHA	2	2	3				U VA		N		
U2N3_BETA	2	0,413	0,587				U		N		
V2ZR	2	2	1				V		ZR		
W2ZR	2	2	1				W		ZR		
ZRPB2	1	1					ZR1PB2				
ZR4PB	1	1					ZR4PB				
ZR5PB3	1	1					ZR5PB3				
ZN22ZR	2	22	1				ZN		ZR		
ZN39Z5	2	39	5				ZN		ZR		
ZN3ZR_LT	2	3	1				ZN		ZR		
ZN3ZR	2	3	1				ZN		ZR		
ZN2ZR	2	2	1				ZN		ZR		
ZNZR	2	1	1				ZN		ZR		

SSOL7 – SGTE Solutions Database: Phase Models List

<i>Phase Name</i>	<i>Number of Sublattices</i>	<i>Stoichiometry</i>					<i>Occupancy</i>				
		<i>SL1</i>	<i>SL2</i>	<i>SL3</i>	<i>SL4</i>	<i>SL5</i>	<i>SL1</i>	<i>SL2</i>	<i>SL3</i>	<i>SL4</i>	<i>SL5</i>
ZNZR3	2	2	2	3			ZN	ZR			
ZNZR2	2	1	2				ZN	ZR			